

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
21 August 2003 (21.08.2003)

PCT

(10) International Publication Number  
WO 03/069961 A1

(51) International Patent Classification: H05B 33/14,  
C09K 11/06, H01L 51/20, C07F 15/00, 9/50, H01L 51/30

(21) International Application Number: PCT/US03/04149

(22) International Filing Date: 11 February 2003 (11.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/356,886 14 February 2002 (14.02.2002) US

(71) Applicant: E.I. DU PONT DE NEMOURS AND COM-  
PANY [US/US]; 1007 Market Street, Wilmington, DE  
19898 (US).

(72) Inventors: GRUSHIN, Vladimir; 533 Runnymede  
Road, Hockessin, DE 19707 (US). PETROV, Viacheslav,  
Alexandrovich; 2 Cappa Court, Hockessin, DE 19707  
(US).

(74) Agent: CAPRIA, Mary, Ann; E.I. Du Pont de Nemours  
and Company, Legal Patent Records Center, 4417 Lan-  
caster Pike, Wilmington, DE 19805 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,  
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC,  
VN, YU, ZA, ZM, ZW.



(84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI,  
SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,  
GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted  
a patent (Rule 4.17(ii)) for the following designations AE,  
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH,  
CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG,  
KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK,  
MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC,

[Continued on next page]

(54) Title: ELECTROLUMINESCENT IRIIDIUM COMPOUNDS WITH PHOSPHINOALKOXIDES AND  
PHENYLPYRIDINES OR PHENYLPYRIMIDINES AND DEVICES MADE WITH SUCH COMPOUNDS



(57) Abstract: The present invention is generally directed to electroluminescent Ir(III) compounds with phosphinoalkoxides and phenylpyridines or phenylpyrimidines, and devices that are made with the Ir(III) compounds.



SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

TITLE

ELECTROLUMINESCENT IRIIDIUM COMPOUNDS WITH  
PHOSPHINOALKOXIDES AND PHENYLPYRIDINES OR  
PHENYLPYRIMIDINES AND DEVICES MADE WITH SUCH  
COMPOUNDS

BACKGROUND OF THE INVENTIONField of the Invention

This invention relates to electroluminescent complexes of  
iridium(III) with phenylpyridines or phenylpyrimidines, which additionally  
have a phosphinoalkoxide ligand. It also relates to electronic devices in  
which the active layer includes an electroluminescent Ir(III) complex.

Description of the Related Art

Organic electronic devices that emit light, such as light-emitting  
diodes that make up displays, are present in many different kinds of  
electronic equipment. In all such devices, an organic active layer is  
sandwiched between two electrical contact layers. At least one of the  
electrical contact layers is light-transmitting so that light can pass through  
the electrical contact layer. The organic active layer emits light through  
the light-transmitting electrical contact layer upon application of electricity  
across the electrical contact layers.

It is well known to use organic electroluminescent compounds as  
the active component in light-emitting diodes. Simple organic molecules  
such as anthracene, thiadiazole derivatives, and coumarin derivatives are  
known to show electroluminescence. Semiconductive conjugated  
polymers have also been used as electroluminescent components, as has  
been disclosed in, for example, Friend et al., U.S. Patent 5,247,190,  
Heeger et al., U.S. Patent 5,408,109, and Nakano et al., Published  
European Patent Application 443 861. Complexes of 8-hydroxyquinolate  
with trivalent metal ions, particularly aluminum, have been extensively  
used as electroluminescent components, as has been disclosed in, for  
example, Tang et al., U.S. Patent 5,552,678.

Burrows and Thompson have reported that fac-tris(2-  
phenylpyridine) iridium can be used as the active component in organic  
light-emitting devices. (*Appl. Phys. Lett.* 1999, 75, 4.) The performance is  
maximized when the iridium compound is present in a host conductive  
material. Thompson has further reported devices in which the active layer  
is poly(N-vinyl carbazole) doped with fac-tris[2-(4',5'-  
difluorophenyl)pyridine-C<sup>2</sup>,N]iridium(III). (*Polymer Preprints* 2000, 41(1),

770.) Additional electroluminescent devices with an active layer of polymer doped with organometallic complexes of iridium have been described by Burrows and Thompson in published PCT applications WO 00/70655 and WO 01/41512. Most of these complexes have emission spectra with peaks in the green or blue-green region.

However, there is a continuing need for electroluminescent compounds having improved efficiency and/or having emission maxima in the blue region of the spectrum.

### SUMMARY OF THE INVENTION

The present invention is directed to an iridium compound having the following Formula I:



where

$\text{L}^a$  and  $\text{L}^b$  are alike or different and each of  $\text{L}^a$  and  $\text{L}^b$  has Formula II, shown in Figure 1, wherein:

$\text{R}^1$  through  $\text{R}^8$  are independently selected from hydrogen, deuterium, alkyl, alkoxy, halogen, nitro, cyano, fluoro,  $\text{C}_n(\text{H}+\text{F})_{2n+1}$ ,  $\text{OC}_n(\text{H}+\text{F})_{2n+1}$ , and  $\text{OCF}_2\text{X}$ , where  $n$  is an integer from 1 through 12, and  $\text{X}$  is H, Cl, or Br, and

$\text{A}$  is C or N, provided that when  $\text{A}$  is N, there is no  $\text{R}^1$ ; and

$\text{L}'$  is a bidentate phosphino alkoxide ligand having Formula III, shown in Figure 2, wherein:

$\text{R}^9$  can be the same or different at each occurrence and is selected from  $\text{C}_m(\text{H}+\text{F})_{2n+1}$ ,  $\text{C}_6(\text{H}+\text{F})_p\text{Y}_{5-p}$ ,

$\text{R}^{10}$  can be the same or different at each occurrence and is selected from H, F, and  $\text{C}_n(\text{H}+\text{F})_{2n+1}$ ;

$\text{Y}$  is  $\text{C}_m(\text{H}+\text{F})_{2m+1}$ ;

$n$  is an integer from 1 through 12;

$m$  is 2 or 3;

$p$  is 0 or an integer from 1 through 5.

In another embodiment, the present invention is directed to phosphinoalkanol precursor compounds from which the phosphinoalkoxide ligands are made. The phosphinoalkanol compounds have Formula III-H, shown in Figure 2, in which  $\text{R}^9$ ,  $\text{R}^{10}$ ,  $\text{Y}$ ,  $n$ ,  $m$ , and  $p$  are as defined above for Formula III.

In another embodiment, the present invention is directed to a process for making a phosphinoalkanol compound.

In another embodiment, the present invention is directed to an organic electronic device having at least one emitting layer comprising the  
5 above Ir(III) compound, or combinations of the above Ir(III) compounds.

As used herein, the term "compound" is intended to mean an electrically uncharged substance made up of molecules that further consist of atoms, wherein the atoms cannot be separated by physical means. The term "ligand" is intended to mean a molecule, ion, or atom  
10 that is attached to the coordination sphere of a metallic ion. The term "complex", when used as a noun, is intended to mean a compound having at least one metallic ion and at least one ligand. The term "group" is intended to mean a part of a compound, such a substituent in an organic compound or a ligand in a complex. The phrase "adjacent to," when used  
15 to refer to layers in a device, does not necessarily mean that one layer is immediately next to another layer. On the other hand, the phrase "adjacent R groups," is used to refer to R groups that are next to each other in a chemical formula (i.e., R groups that are on atoms joined by a bond). The term "photoactive" refers to any material that exhibits  
20 electroluminescence and/or photosensitivity. The term "(H+F)" is intended to mean all combinations of hydrogen and fluorine, including completely hydrogenated, partially fluorinated or perfluorinated substituents. By "emission maximum" is meant the wavelength, in nanometers, at which the maximum intensity of electroluminescence is obtained.  
25 Electroluminescence is generally measured in a diode structure, in which the material to be tested is sandwiched between two electrical contact layers and a voltage is applied. The light intensity and wavelength can be measured, for example, by a photodiode and a spectrograph, respectively. In addition, the IUPAC numbering system is used throughout, where the  
30 groups from the Periodic Table are numbered from left to right as 1 through 18 (CRC Handbook of Chemistry and Physics, 81<sup>st</sup> Edition, 2000).

#### DESCRIPTION OF THE DRAWINGS

Figure 1 shows Formula II for phenylpyridine and phenylpyrimidine ligands useful in the metal complex of the invention, and Formula II-H for  
35 the ligand precursor compound.

Figure 2 shows Formula III for phosphinoalkanoxy ligands useful in the metal complex of the invention, and Formula III-H for the ligand precursor compound.

Figure 3 shows Equation 1 for forming the ligand precursor compound, II-H.

Figure 4 shows Equation 2 for forming the ligand precursor compound, III-H.

5 Figure 5 shows Formulae IV and V for bridged-Ir dimers.

Figure 6 is a schematic diagram of a light-emitting device (LED).

Figure 7 is a schematic diagram of an LED testing apparatus.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

10 The Ir(III) compounds of the invention have Formula I, as defined above. The compounds are frequently referred to as bis-cyclometalated complexes. The cyclometalated complexes of the invention are neutral and non-ionic, and can be sublimed intact. Thin films of these materials obtained via vacuum deposition exhibit good to excellent electroluminescent properties.

15 Two of the ligands in the Ir(III) compounds of the invention, are phenylpyridine or phenylpyrimidine ligands having Formula II, shown in Figure 1. The R<sup>1</sup> through R<sup>8</sup> groups of Formula II may be chosen from conventional substituents for organic compounds, such as alkyl, alkoxy, halogen, nitro, and cyano groups, as well as fluoro, fluorinated alkyl and  
20 fluorinated alkoxy groups. The groups can be partially or fully fluorinated (perfluorinated).

The precursor 2-phenylpyridines and 2-phenylpyrimidines, Formula II-H in Figure 1, are prepared, in good to excellent yield, using the Suzuki coupling of the substituted 2-chloropyridine or 2-chloropyrimidine with  
25 arylboronic acid as described in O. Lohse, P.Thevenin, E. Waldvogel *Synlett*, 1999, 45-48. This reaction is illustrated for the pyridine derivative, where X and Y represent substituents, in Equation (1) shown in Figure 3.

Examples of 2-phenylpyridine and 2-phenylpyrimidine compounds, having Formula II-H, are given in Table 1 below:

30

TABLE 1										
Compound	A	R <sub>1</sub>	R <sub>2</sub>	R <sub>3</sub>	R <sub>4</sub>	R <sub>5</sub>	R <sub>6</sub>	R <sub>7</sub>	R <sub>8</sub>	R <sub>9</sub>
1-a	C	H	H	CF <sub>3</sub>	H	F	H	H	H	H
1-b	C	H	H	CF <sub>3</sub>	H	H	CF <sub>3</sub>	H	H	H
1-c	C	H	H	NO <sub>2</sub>	H	H	CF <sub>3</sub>	H	H	H
1-d	C	H	H	CF <sub>3</sub>	H	H	F	H	H	H
1-e	C	H	H	CF <sub>3</sub>	H	H	H	CH <sub>3</sub> O	H	H

TABLE 1										
1-f	C	Cl	H	CF <sub>3</sub>	H	H	H	H	H	H
1-g	C	H	H	H	CH <sub>3</sub>	H	H	F	H	H
1-h	N	—	H	H	H	H	H	F	H	H
1-i	C	H	H	CF <sub>3</sub>	H	H	H	CF <sub>3</sub> O	H	H
1-j	N	—	CF <sub>3</sub>	H	H	F	H	H	H	H
1-k	C	H	H	CF <sub>3</sub>	H	H	H	F	H	H
1-l	C	CF <sub>3</sub>	H	H	H	H	H	H	H	H
1-m	C	Cl	H	CF <sub>3</sub>	H	H	H	F	H	H
1-n	C	CF <sub>3</sub>	H	H	H	H	H	F	H	H
1-o	C	CF <sub>3</sub>	H	H	H	H	H	CH <sub>3</sub> O	H	H
1-p	C	Cl	H	CF <sub>3</sub>	H	H	H	CH <sub>3</sub> O	H	H
1-q	N	—	CF <sub>3</sub>	H	H	H	H	F	H	H
1-r	C	Cl	H	CF <sub>3</sub>	H	H	H	H	H	H
1-s	C	H	H	CF <sub>3</sub>	H	H	H	H	H	H
1-t	C	Cl	H	H	H	F	H	H	H	H
1-v	C	H	H	CF <sub>3</sub>	H	H	CH <sub>3</sub> O	H	H	H
1-w	C	H	CH <sub>3</sub> O	H	H	H	H	CF <sub>3</sub>	H	H
1-x	C	H	H	H	H	H	F	F	H	H
1-y	C	H	H	CF <sub>3</sub>	H	H	F	H	F	H
1-z	C	H	H	CF <sub>3</sub>	H	F	H	F	H	H
1-aa	C	H	H	Br	H	H	H	Br	H	H
1-ab	C	H	CH <sub>3</sub>	H	H	F	H	F	H	H
1-ac	C	H	CH <sub>3</sub>	H	H	H	CF <sub>3</sub>	H	CF <sub>3</sub>	H
1-ad	C	H	H	CH <sub>3</sub>	H	F	H	F	H	H
1-ae	C	H	CH <sub>3</sub>	H	H	H	CF <sub>3</sub>	H	H	H
1-af	C	H	H	CH <sub>3</sub>	H	H	CF <sub>3</sub>	H	CF <sub>3</sub>	H
1-ag	C	H	H	H	H	H	CF <sub>3</sub>	H	H	H
1-ah	C	H	H	H	H	F	H	F	H	H
1-ai	C	H	t-Bu	H	H	F	H	F	H	H
1-aj	C	H	t-Bu	H	H	H	CF <sub>3</sub>	H	CF <sub>3</sub>	H
1-ak	C	H	CH <sub>3</sub>	H	H	H	H	CF <sub>3</sub>	H	H
1-al	C	H	H	H	H	CH <sub>3</sub> O	H	CH <sub>3</sub> O	H	H

where "t-Bu" represents a tertiary butyl group.

The third ligand in the Ir(III) compounds of the invention is a phosphinoalkoxide. The precursor phosphinoalkanol compounds having

5 Formula III-H, as shown in Figure 2, can be prepared using known

procedures, such as, for example, the procedure reported in *Inorg. Chem.* **1985**, v.24, p.3680, for 1,1-bis(trifluoromethyl)-2-(diphenylphosphino)ethanol. This method involves the reaction of diphenylphosphinomethylithium with hexafluoroacetylacetone, followed by hydrolysis.

Alternatively, the phosphino alkanol compounds can be prepared using the reaction of 1,1-bis(trifluoromethyl)ethylene oxide with the corresponding secondary phosphine ( $R^9_2PH$ ) or its deprotonated form as a salt ( $[R^9_2P]M$ ), where M is Li, Na, or K. The deprotonated form can be prepared by the treatment of the secondary phosphine with a strong base, such as BuLi or t-BuOK.

Alternatively, the phosphino alkanol compounds can be made using dilithiated derivatives of halohydrins, which can be prepared as described in *J. Chem. Soc., Perkin Trans. 1*, **1983**, p. 3019. The dilithio-derivative is reacted with a chlorophosphine to produce the desired phosphinoalkanol ligand. Halohydrins are made by a variety of literature methods, such as ring-opening of an epoxide (also called an "oxirane") with HHal (Hal = Cl, Br, I; see: *J. Am. Chem. Soc.* **1960**, vol. 82, p. 2288). This is particularly useful for 1,1-bis(trifluoromethyl)ethylene oxide which can be prepared as described in Petrov, V. A. et al., WO 00/66575, PCT/US00/11746, Chem. Abstr. 2000, 350691. In the process of the invention, a dried bromohydrin is combined with n-butyl lithium, wherein the molar ratio of n-butyl lithium to bromohydrin is about 2. The preferred process for preparing the phosphino alkanol comprises the steps:

(1) combining an epoxide with aqueous HBr, to form a bromohydrin;  
(2) isolating the bromohydrin from step (1) and removing water;  
(3) combining the dried bromohydrin from step (2) with n-butyl lithium, wherein the molar ratio of n-butyl lithium to the bromohydrin is about 2;

(4) adding a chlorophosphine to the product of step (3); and  
(5) adding acid to the product of step (4).

The epoxide can be substituted with groups such as alkyl, partially fluorinated alkyl, and perfluoroalkyl groups; preferably trifluoromethyl groups. The chlorophosphine is a chlorodialkylphosphine or a chlorodialkylphosphine; preferably, chlorodiphenylphosphine. The acid can be any Bronsted acid which will provide a proton in the last reaction step, preferably trifluoroacetic acid. The reaction scheme is illustrated using bis(trifluoromethyl)ethylene oxide in Equation (2), shown in Figure 4. The



dilithiation of the bromohydrin deriving from bis(trifluoromethyl)ethylene oxide can be done with 2 equivalents of BuLi within 0.5 h at -78 °C. This is different from the literature procedure (*J. Chem. Soc., Perkin Trans. 1*, 1983, p. 3019) which employs 1 equivalent of BuLi for 3 hours, followed by  
 5 1 equivalent of naphthyl lithium for 5 hours at -78 °C. Naphthyl lithium is not commercially available and is more expensive to make. The process of the invention is, in general, faster and uses readily available butyl lithium.

In the preferred phosphinoalkanol of Formula III-H, R<sup>9</sup> is C<sub>6</sub>F<sub>5</sub> or C<sub>6</sub>H<sub>p</sub>Y<sub>5-p</sub>, where Y is CF<sub>3</sub> and p is 3 or 4. Preferably at least one of R<sup>10</sup> is  
 10 CF<sub>3</sub> and m is 2.

Examples of suitable phosphinoalkanol compounds, with the abbreviation in brackets, include:

- 1-diphenylphosphino-2-propanol [dppOH]
- 1-bis(trifluoromethyl)-2-(diphenylphosphino)ethanol [PO-1H]
- 15 1,1-bis(trifluoromethyl)-2-(bis(3'5'-  
ditrifluoromethylphenyl)phosphino)ethanol [PO-2H]
- 1,1-bis(trifluoromethyl)-2-(bis(4'-  
trifluoromethylphenyl)phosphino)ethanol [PO-3H]
- 1,1-bis(trifluoromethyl)-2-(bis(pentafluorophenyl)phosphino)ethanol  
 20 [PO-4H]

The phosphinoalkoxide ligands from the above compounds are, respectively (abbreviations provided in brackets):

- 1-diphenylphosphino-2-propoxide [dppO]
- 1-bis(trifluoromethyl)-2-(diphenylphosphino)ethoxide [PO-1]
- 25 1,1-bis(trifluoromethyl)-2-(bis(3'5'-  
ditrifluoromethylphenyl)phosphino)ethoxide [PO-2]
- 1,1-bis(trifluoromethyl)-2-(bis(4'-  
trifluoromethylphenyl)phosphino)ethoxide [PO-3]
- 1,1-bis(trifluoromethyl)-2-  
 30 (bis(pentafluorophenyl)phosphino)ethoxide [PO-4]

The iridium complexes of the invention can be prepared by first preparing an intermediate iridium dimer with the phenylpyridine or phenypyrimidine ligand. The dimer can be the dichloro bridged dimer having Formula IV, shown in Figure 5, or the dihydroxo bridged dimer having Formula V, shown in Figure 5, where:

in Formulae IV and V:

$L^a, L^b, L^c$ , and  $L^d$  can be the same or different from each other and each of  $L^a, L^b, L^c$ , and  $L^d$  has Formula II, as defined above;

in Formula V:

5  $B = H, CH_3, \text{ or } C_2H_5.$

The dichloro bridged dimers having Formula IV, can generally be prepared by reacting iridium trichloride hydrate with the 2-phenylpyridine or 2-phenylpyrimidine in a suitable solvent, such as 2-ethoxyethanol. The iridium bridged dimers having Formula V, can generally be prepared by  
 10 reacting iridium trichloride hydrate with the 2-phenylpyridine or 2-phenylpyrimidine, and then adding NaOB. These dicyclopentametalated complexes can be isolated and (optionally) purified before the reaction with the phosphinoalkanols or used without isolation, as described in the examples below. The chloro dicyclopentametalated complexes can react, under  
 15 biphasic or homogeneous conditions, with either the phosphinoalkanols in the presence of a base, such as NaOH, or salts of the phosphinoalkanols. When salts of the phosphinoalkanols are used with the dichloro bridged dimers, and also when intermediates having Formula V are used, no additional base is required for the synthesis.

20 Examples of compounds having Formula I, where  $L^a$  is the same as  $L^b$ , are given in Table 2 below, where  $R^1$  through  $R^8$  are as shown in Formula I, and A is C.

Table 2.									
Comp.	$L'$	$R^1$	$R^2$	$R^3$	$R^4$	$R^5$	$R^6$	$R^7$	$R^8$
2-a	PO-1	H	$CH_3$	H	H	F	H	F	H
2-b	PO-2	H	$CH_3$	H	H	F	H	F	H
2-c	PO-1	H	H	H	H	F	H	F	H
2-d	PO-2	H	H	H	H	F	H	F	H
2-e	PO-1	H	H	H	H	H	$CF_3$	H	H
2-f	PO-1	H	$CH_3$	H	H	H	$CF_3$	H	$CF_3$
2-g	PO-2	H	$CH_3$	H	H	H	$CF_3$	H	$CF_3$
2-h	PO-1	H	H	$CH_3$	H	F	H	F	H
2-i	PO-2	H	H	$CH_3$	H	F	H	F	H

Table 2.									
2-j	PO-1	H	H	CF <sub>3</sub>	H	H	H	F	H
2-k	PO-1	H	t-Bu	H	H	F	H	F	H
2-l	PO-1	H	t-Bu	H	H	H	CF <sub>3</sub>	H	CF <sub>3</sub>
2-m	PO-3	H	H	CH <sub>3</sub>	H	F	H	F	H
2-n	PO-3	H	CH <sub>3</sub>	H	H	F	H	F	H
2-o	PO-1	H	H	H	H	CH <sub>3</sub> O	H	CH <sub>3</sub> O	H
2-p	PO-2	H	H	H	H	CH <sub>3</sub> O	H	CH <sub>3</sub> O	H
2-q	PO-1	H	CH <sub>3</sub>	H	H	H	CF <sub>3</sub>	H	H
2-r	PO-2	H	CH <sub>3</sub>	H	H	H	CF <sub>3</sub>	H	H
2-s	PO-1	H	CH <sub>3</sub>	H	H	H	H	CF <sub>3</sub>	H
2-t	PO-4	H	CH <sub>3</sub>	H	H	H	CF <sub>3</sub>	H	CF <sub>3</sub>
2-u	PO-4	H	CH <sub>3</sub>	H	H	F	H	F	H
2-v	PO-2	H	H	H	H	H	H	H	H

where "t-Bu" represents a tertiary butyl group.

#### Electronic Device

The present invention also relates to an electronic device comprising at least one photoactive layer positioned between two electrical contact layers, wherein the at least one layer of the device includes the iridium complex of the invention. Devices frequently have additional hole transport and electron transport layers. A typical structure is shown in Figure 1. The device 100 has an anode layer 110 and a cathode layer 150. Adjacent to the anode is a layer 120 comprising hole transport material. Adjacent to the cathode is a layer 140 comprising an electron transport material. Between the hole transport layer and the electron transport layer is the photoactive layer 130. Layers 120, 130, and 140 are individually and collectively referred to as the active layers.

Depending upon the application of the device 100, the photoactive layer 130 can be a light-emitting layer that is activated by an applied voltage (such as in a light-emitting diode or light-emitting electrochemical cell), a layer of material that responds to radiant energy and generates a signal with or without an applied bias voltage (such as in a photodetector). Examples of photodetectors include photoconductive cells, photoresistors, photoswitches, phototransistors, and phototubes, and photovoltaic cells,

as these terms are describe in Markus, John, *Electronics and Nucleonics Dictionary*, 470 and 476 (McGraw-Hill, Inc. 1966).

The iridium compounds of the invention are particularly useful as the photoactive material in layer 130, or as electron transport material in layer 140. Preferably the iridium complexes of the invention are used as the light-emitting material in diodes. It has been found that in these applications, the compounds of the invention do not need to be in a solid matrix diluent in order to be effective. A layer that is greater than 20% by weight iridium compound, based on the total weight of the layer, up to 100% iridium compound, can be used as the emitting layer. Additional materials can be present in the emitting layer with the iridium compound. For example, a fluorescent dye may be present to alter the color of emission. A diluent may also be added. The diluent can be a polymeric material, such as poly(N-vinyl carbazole) and polysilane. It can also be a small molecule, such as 4,4'-N,N'-dicarbazole biphenyl or tertiary aromatic amines. When a diluent is used, the iridium compound is generally present in a small amount, usually less than 20% by weight, preferably less than 10% by weight, based on the total weight of the layer.

In some cases the iridium complexes may be present in more than one isomeric form, or mixtures of different complexes may be present. It will be understood that in the above discussion of OLEDs, the term "the iridium compound" is intended to encompass mixtures of compounds and/or isomers.

To achieve a high efficiency LED, the HOMO (highest occupied molecular orbital) of the hole transport material should align with the work function of the anode, the LUMO (lowest un-occupied molecular orbital) of the electron transport material should align with the work function of the cathode. Chemical compatibility and sublimation temp of the materials are also important considerations in selecting the electron and hole transport materials.

The other layers in the OLED can be made of any materials which are known to be useful in such layers. The anode 110, is an electrode that is particularly efficient for injecting positive charge carriers. It can be made of, for example materials containing a metal, mixed metal, alloy, metal oxide or mixed-metal oxide, or it can be a conducting polymer. Suitable metals include the Group 11 metals, the metals in Groups 4, 5, and 6, and the Group 8-10 transition metals. If the anode is to be light-transmitting, mixed-metal oxides of Groups 12, 13 and 14 metals, such as indium-tin-

oxide, are generally used. The anode 110 may also comprise an organic material such as polyaniline as described in "Flexible light-emitting diodes made from soluble conducting polymer," *Nature* vol. 357, pp 477-479 (11 June 1992). At least one of the anode and cathode should be at least

5 partially transparent to allow the generated light to be observed.

Examples of hole transport materials for layer 120 have been summarized for example, in Kirk-Othmer Encyclopedia of Chemical Technology, Fourth Edition, Vol. 18, p. 837-860, 1996, by Y. Wang. Both hole transporting molecules and polymers can be used. Commonly used

10 hole transporting molecules are: N,N'-diphenyl-N,N'-bis(3-methylphenyl)-[1,1'-biphenyl]-4,4'-diamine ("TPD"), 1,1-bis[(di-4-tolylamino)phenyl]cyclohexane ("TAPC"), N,N'-bis(4-methylphenyl)-N,N'-bis(4-ethylphenyl)-[1,1'-(3,3'-dimethyl)biphenyl]-4,4'-diamine ("ETPD"), tetrakis-(3-methylphenyl)-N,N,N',N'-2,5-phenylenediamine ("PDA"), a-

15 phenyl-4-N,N-diphenylaminostyrene ("TPS"), p-(diethylamino)-benzaldehyde diphenylhydrazone ("DEH"), triphenylamine ("TPA"), bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)methane ("MPMP"), 1-phenyl-3-[p-(diethylamino)styryl]-5-[p-(diethylamino)phenyl]pyrazoline ("PPR" or "DEASP"), 1,2-trans-bis(9H-carbazol-9-

20 yl)cyclobutane ("DCZB"), N,N,N',N'-tetrakis(4-methylphenyl)-(1,1'-biphenyl)-4,4'-diamine ("TTB"), and porphyrinic compounds, such as copper phthalocyanine. Commonly used hole transporting polymers are polyvinylcarbazole, (phenylmethyl)polysilane, and polyaniline. It is also possible to obtain hole transporting polymers by doping hole transporting

25 molecules such as those mentioned above into polymers such as polystyrene and polycarbonate.

Examples of electron transport materials for layer 140 include metal chelated oxinoid compounds, such as tris(8-hydroxyquinolato)aluminum ("Alq<sub>3</sub>"); phenanthroline-based compounds, such as 2,9-dimethyl-4,7-

30 diphenyl-1,10-phenanthroline ("DDPA") or 4,7-diphenyl-1,10-phenanthroline ("DPA"), and azole compounds such as 2-(4-biphenyl)-5-(4-t-butylphenyl)-1,3,4-oxadiazole ("PBD") and 3-(4-biphenyl)-4-phenyl-5-(4-t-butylphenyl)-1,2,4-triazole ("TAZ"). Layer 140 can function both to facilitate electron transport, and also serve as a buffer layer or

35 confinement layer to prevent quenching of the exciton at layer interfaces. Preferably, this layer promotes electron mobility and reduces exciton quenching.

The cathode 150, is an electrode that is particularly efficient for injecting electrons or negative charge carriers. The cathode can be any metal or nonmetal having a lower work function than the anode. Materials for the cathode can be selected from alkali metals of Group 1 (e.g., Li, Cs), the Group 2 (alkaline earth) metals, the Group 12 metals, including the rare earth elements and lanthanides, and the actinides. Materials such as aluminum, indium, calcium, barium, samarium and magnesium, as well as combinations, can be used. Li-containing organometallic compounds can also be deposited between the organic layer and the cathode layer to lower the operating voltage.

It is known to have other layers in organic electronic devices. For example, there can be a layer (not shown) between the conductive polymer layer 120 and the active layer 130 to facilitate positive charge transport and/or band-gap matching of the layers, or to function as a protective layer. Similarly, there can be additional layers (not shown) between the active layer 130 and the cathode layer 150 to facilitate negative charge transport and/or band-gap matching between the layers, or to function as a protective layer. Layers that are known in the art can be used. In addition, any of the above-described layers can be made of two or more layers. Alternatively, some or all of inorganic anode layer 110, the conductive polymer layer 120, the active layer 130, and cathode layer 150, may be surface treated to increase charge carrier transport efficiency. The choice of materials for each of the component layers is preferably determined by balancing the goals of providing a device with high device efficiency.

It is understood that each functional layer may be made up of more than one layer.

The device can be prepared by sequentially vapor depositing the individual layers on a suitable substrate. Substrates such as glass and polymeric films can be used. Conventional vapor deposition techniques can be used, such as thermal evaporation, chemical vapor deposition, and the like. Alternatively, the organic layers can be coated from solutions or dispersions in suitable solvents, using any conventional coating technique. In general, the different layers will have the following range of thicknesses: anode 110, 500-5000Å, preferably 1000-2000Å; hole transport layer 120, 50-1000Å, preferably 200-800Å; light-emitting layer 130, 10-1000 Å, preferably 100-800Å; electron transport layer 140, 50-1000Å, preferably 200-800Å; cathode 150, 200-10000Å, preferably 300-5000Å. The location

of the electron-hole recombination zone in the device, and thus the emission spectrum of the device, can be affected by the relative thickness of each layer. Thus the thickness of the electron-transport layer should be chosen so that the electron-hole recombination zone is in the light-emitting layer. The desired ratio of layer thicknesses will depend on the exact nature of the materials used.

It is understood that the efficiency of devices made with the iridium compounds of the invention, can be further improved by optimizing the other layers in the device. For example, more efficient cathodes such as Ca, Ba or LiF can be used. Shaped substrates and novel hole transport materials that result in a reduction in operating voltage or increase quantum efficiency are also applicable. Additional layers can also be added to tailor the energy levels of the various layers and facilitate electroluminescence.

The iridium complexes of the invention are phosphorescent and photoluminescent and may be useful in applications other than OLEDs. For example, organometallic complexes of iridium have been used as oxygen sensitive indicators, as phosphorescent indicators in bioassays, and as catalysts.

#### EXAMPLES

The following examples illustrate certain features and advantages of the present invention. They are intended to be illustrative of the invention, but not limiting. All percentages are by weight, unless otherwise indicated.

#### EXAMPLE 1

This example illustrates the preparation of the 2-phenylpyridines and 2-phenylpyrimidines which are used to form the iridium compounds.

The general procedure used was described in O. Lohse, P. Thevenin, E. Waldvogel *Synlett*, 1999, 45-48. In a typical experiment, a mixture of 200 ml of degassed water, 20 g of potassium carbonate, 150 ml of 1,2-dimethoxyethane, 0.5 g of Pd(PPh<sub>3</sub>)<sub>4</sub>, 0.05 mol of a substituted 2-chloropyridine (quinoline or pyrimidine) and 0.05 mol of a substituted phenylboronic acid was refluxed (80-90°C) for 16-30 h. The resulting reaction mixture was diluted with 300 ml of water and extracted with CH<sub>2</sub>Cl<sub>2</sub> (2 x 100 ml). The combined organic layers were dried over MgSO<sub>4</sub>, and the solvent removed by vacuum. The liquid products were purified by fractional vacuum distillation. The solid materials were

recrystallized from hexane. The typical purity of isolated materials was >98%.

2-(2',4'-dimethoxyphenyl)pyridine was prepared via Kumada coupling of 2-chloropyridine with 2,4-dimethoxyphenylmagnesium bromide in the presence of [(dppb)PdCl<sub>2</sub>] catalyst, where dppb represents 1,4-bis(diphenylphosphino)butane).

The starting materials, yields, melting and boiling points of the new materials are given in Table 3. NMR data and analytical data are given in Table 4.

10

**TABLE 3**  
**Preparation of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines**

Compound	Yield in %	B.p./ mm Hg (m.p.) in °C
1-s	70	---
1-a	72	---
1-b	48	---
1-u	75	(76-78)
1-c	41	(95-96)
1-d	38	(39-40)
1-e	55	74.5/0.1
1-g	86	71-73/0.07
1-t	65	77-78/0.046
1-k	50	(38-40)
1-m	80	72-73/0.01
1-f	22	52-33/0.12
1-v	63	95-96/13
1-w	72	
1-x	35	61-62/0.095
1-y	62	(68-70)
1-z	42	66-67/0.06 (58-60)
1-aa	60	
1-ab	61.5	70-72/0.03
1-ac	39	66-68/0.01
1-ad	76	75-76/0.01 (54-56)
1-ae	76	69-70/0.06 (44-46)
1-af	84	(83-85)
1-ag	72	64-65/0.026
1-ah	36	62/0.01
1-ai	49	99-101/0.26
1-aj	58	108-109/0.1



**TABLE 3****Preparation of 2-Phenyl Pyridines, Phenylpyrimidines and****Phenylquinolines**

1-ak	46	76-77/01 (52-54)
------	----	---------------------

**TABLE 4****Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines**

Compound	<sup>1</sup> H NMR	<sup>19</sup> F NMR	Analysis %, found (calc.) or MS (M <sup>+</sup> )
1-s	7.48(3H), 7.70(1H), 7.83(1H), 7.90(2H), 8.75(1H)	-62.68	C, 64.50 (64.57) H, 3.49 (3.59) N, 6.07 (6.28)
1-a	7.19(1H), 7.30(1H), 7.43(1H), 7.98(2H), 8.07 (1H) 9.00(1H)	-60.82 (3F, s), -116.96 (1F, m)	C, 59.56 (59.75) H, 3.19 (2.90) N, 5.52 (5.81)
1-b	7.58(1H), 7.66(1H), 7.88(1H), 8.03(1H), 8.23(1H), 8.35 (1H) 8.99(1H)	-62.75 (3F, s), -63.10 (3F, s)	C, 53.68 (53.60) H, 2.61 (2.40) N, 4.53 (4.81)
1-u	7.55(1H), 7.63(1H), 7.75(2H), 7.89(2H), 8.28(2H), 8.38(1H), 8.50 (1H)	-62.89 (s)	C, 69.17 (70.33) H, 3.79 (3.66) N, 4.88 (5.12)
1-c	7.53(1H), 7.64(1H), 7.90(1H), 8.18(1H), 8.30(1H), 8.53(1H), 9.43(1H)	-62.14 (s)	C, 53.83 (53.73) H, 2.89 (2.61) N, 9.99 (10.44)
1-d	7.06(1H), 7.48(1H), 7.81(3H), 8.01(1H), 8.95(1H),	-62.78 (3F, s), -112.61 (1F, m)	C, 59.73 (59.75) H, 2.86 (2.90) N, 5.70 (5.81)

TABLE 4

## Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	<sup>1</sup> H NMR	<sup>19</sup> F NMR	Analysis %, found (calc.) or MS (M <sup>+</sup> )
1-e	3.80(3H), 6.93(2H), 7.68(1H), 7.85(1H), 7.96(2H), 8.82(1H),	-62.63 (s)	C, 61.66 (61.90) H, 3.95 (4.04) N, 5.53 (5.38)
1-g	2.70(3H), 7.10(3H), 7.48(1H), 7.60(1H), 8.05(2H),	-114.03 (m)	C, 76.56 (77.00) H, 5.12 (5.30) N, 5.43 (7.50)
1-t	7.10(2H), 7.35(2H), 7.96(1H), 8.78(1H),	-62.73 (3F, s) -113.67 (1F, m)	C, 50.51 (52.17) H, 1.97 (2.17) N, 5.09 (5.07)
1-k	7.08(2H), 7.62(1H), 7.90(3H), 8.80(1H),	-62.75 (3F, s) -111.49 (m)	C, 60.39 (59.75), H, 3.38 (2.90), N, 5.53 (5.51)
1-m	7.10(2H), 7.80(2H), 8.00(1H), 8.75(1H),	-62.63 (3F, s) -111.24 (m)	C, 52.13 (52.17) H, 2.16 (2.17) N, 4.85 (5.07)
1-f	7.55(3H), 7.77(2H), 8.06(1H), 8.87(1H)	-62.57(s)	257(M <sup>+</sup> , C <sub>12</sub> H <sub>7</sub> F <sub>3</sub> ClN <sup>+</sup> ), 222(M-Cl)
1-v	3.8(3H), 6.95(1H), 7.30(1H), 7.50(1H), 7.58(1H), 7.75(1H), 7.90(1H), 8.87(1H)	-62.70 ppm	C, 61.66 (61.37), H, 3.98 (3.67), N, 5.53 (5.48)

TABLE 4

## Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines

Compound	<sup>1</sup> H NMR	<sup>19</sup> F NMR	Analysis %, found (calc.) or MS (M <sup>+</sup> )
1-w	8.54 (1H, d), 8.21 (2H, d), 7.70 (2H, d), 7.24 (1H, s), 6.82 (1H, dd), 3.91 (3H, s)	-63.08 (3F, s)	
1-x	6.9 (2H, m), 7.18 (2H, m), 7.68 (2H, m), 7.95 (1H, m), 8.65 (1H, m);	-109.70 (1F, m), -113.35 (1F, m).	
1-y	6.94 (1H), 7.62 (2H), 7.82 (1H), 8.03 (1H), 8.96 (1H);	-62.72 (3F, s), -109.11 (2F, m)	
1-z	6.85 (1H), 6.93 (1H), 7.80, 7.90, 8.05 (3H), 8.89 (1H);	-62.80 (3F, s), -107.65 (1F, m), -112.45 (1F, m).	
1-aa	7.70 (3H, m), 7.85 (3H, m), 7.80, 7.90, 8.85 (1H, m).		
1-ab	2.39 (3H), 6.99 (2H), 7.02 (1H), 7.57 (1H), 7.99 (1H), 8.56 (1H)	-102.96 (1F, m), -113.18 (1F, m)	

**TABLE 4****Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines**

Compound	<sup>1</sup> H NMR	<sup>19</sup> F NMR	Analysis %, found (calc.) or MS (M <sup>+</sup> )
1-ac	2.47(3H), 7.17(1H), 7.63(1H), 7.91(1H), 8.48(2H), 8.60 (1H), 9.00(1H)	-63.23 (s)	
1-ad	2.25(3H), 6.90(2H), 7.55(2H), 8.50(1H), 8.85(1H),	-110.37 (1F, m) -113.50 (1F,m)	
1-ae	2.35(3H), 7.05(1H), 7.55(2H), 8.01(1H), 8.18(1H), 8.50(1H)	-63.03 (s)	
1-af	2.43(3H) 7.66(1H), 7.87(1H), 8.47(2H), 8.59 (1H)	-63.18 (s)	
1-ag	7.20(1H), 7.65(3H), 8.10(1H), 8.17(1H), 8.65(1H), 9.43(1H)	-63.05 (s)	
1-ah	6.90(1H), 7.18(2H), 7.68(2H), 7.95(1H), 8.65(1H),	-109.70 (1F, m) -113.35 (1F, m)	

**TABLE 4****Properties of 2-Phenyl Pyridines, Phenylpyrimidines and Phenylquinolines**

Compound	<sup>1</sup> H NMR	<sup>19</sup> F NMR	Analysis %, found (calc.) or MS (M <sup>+</sup> )
1-aj	1.35(9H) 7.34(1H) 7.72(1H) 7.88(1H) 8.44(2H) 8.61(1H)	-63.19	
1-ak	2.46(3H) 7.15(1H) 7.60(1H) 7.73(2H) 8.11(2H) 8.59(1H)	-62.86	

Compound 1-al has been reported previously in the literature.

**EXAMPLES 2-4**

These examples illustrate the preparation of the phosphinoalkanol precursor compounds.

5

**EXAMPLE 2**

This example illustrates the preparation of the precursor compound 1,1-bis(trifluoromethyl)-2-bis(triphenylphosphino)-ethanol (PO-1H). The compound was made by two different methods.

**Method a:**

- 10 The phosphino alkanol was made according to the procedure in Inorg. Chem. (1985), 24(22), pp. 3680-7. Under nitrogen, 1,1-bis(trifluoromethyl)ethylene oxide (12 g, 0.066 mol) was added dropwise to a pre-cooled (10-15 °C) solution of diphenylphosphine (10g, 0.053 mol) in dry THF (50 mL). The reaction mixture was stirred at 25°C for 2 days,
- 15 after which NMR analysis indicated > 90% conversion. The solvent was removed under vacuum and the residual viscous oil was distilled under vacuum to give 8 g of the fraction (b.p. 110-114 °C at 0.05 mm Hg) which crystallized on standing. Both the NMR data and m.p. (59-62 °C) of this material (>95% purity) were consistent with those reported in: Boere, R. T.
- 20 et al., Inorg. Chem. (1985), 24, 3680. <sup>1</sup>H NMR (CDCl<sub>3</sub>, 20 °C), δ: 7.3-7.8 (m, 10H, arom. H); 2.8 (br. s.; 1H, OH); 2.2 (s, 2H, CH<sub>2</sub>). <sup>19</sup>F NMR (CDCl<sub>3</sub>, 20 °C), δ: -77.3 (d, J<sub>F-P</sub> = 15.5 Hz). <sup>31</sup>P NMR (CDCl<sub>3</sub>, 20 °C), δ: -24.4 (septet, J<sub>P-F</sub> = 15.5 Hz).

**Method b:**

- 25 (i) Preparation of 1,1-bis(trifluoromethyl)-2-bromoethanol, BrCH<sub>2</sub>C(CF<sub>3</sub>)<sub>2</sub>OH. 1,1-bis(trifluoromethyl)oxirane (100 g; 0.55 mol;

prepared as described in WO 00/66575, 2000, to DuPont). was added slowly to 100 ml of 47% aqueous HBr placed in a round bottom glass flask equipped with a dry-ice condenser, thermometer, and magnetic stir bar at 30–40°C. The reaction mixture was stirred under reflux for 3 h. At that point the temperature raised to 90 °C. After cooling to room temperature, the bottom layer was separated, dried over MgSO<sub>4</sub>, and distilled to give 104 g (72%) of BrCH<sub>2</sub>C(CF<sub>3</sub>)<sub>2</sub>OH, b.p. 101–103°C. <sup>1</sup>H NMR (CDCl<sub>3</sub>): 3.50 (br s, 1H, -OH), 3.70(s, 2H, CH<sub>2</sub>). <sup>19</sup>F NMR (CDCl<sub>3</sub>): -75.9 (s). This material was dried over freshly calcined molecular sieves (4 Å) prior to the next step.

(ii) Under nitrogen, to a stirring solution of 1,1-bis(trifluoromethyl)-2-bromoethanol (5.64 g; prepared as described above) in dry ether (110 mL) cooled to -78 °C, was added drop-wise 1.6 M n-BuLi in hexanes (Aldrich; 27 mL). After 1 h at -78 °C, chlorodiphenylphosphine (Strem; 4.53 g) was added drop-wise, at vigorous stirring, to the resulting solution of the dilithiated derivative. After stirring the mixture for 3 h 20 min at -78 °C, it was allowed to warm slowly to room temperature and then stirred at room temperature overnight. The solvents were removed under vacuum. Dichloromethane (10 mL) and trifluoroacetic acid (1.66 mL) were added to the residue, and the mixture was chromatographed on a silica gel column (5 x 25 cm) with dichloromethane. The product was isolated as an oil which crystallized upon drying under vacuum. The yield of the product as white crystalline solid was 5.3 g (71%). The compound was found identical with the material synthesized according to method a.

1,1-bis(trifluoromethyl)-2-bis(triphenylphosphino)-ethoxide [PO-1]

To make the sodium salt of the ethoxide ligand PO-1, sodium hydride was added to the alcohol in THF. The salt was isolated by removing the volatile components in vacuo.

EXAMPLE 3

This example illustrates the preparation of the phosphinoalkanol precursor compound Ar<sub>2</sub>PCH<sub>2</sub>C(OH)(CF<sub>3</sub>)<sub>2</sub>, where Ar = 3,5-(CF<sub>3</sub>)<sub>2</sub>C<sub>6</sub>H<sub>3</sub> [PO-2H].

Method a:

Under nitrogen, a stirring solution of (3,5-(CF<sub>3</sub>)<sub>2</sub>C<sub>6</sub>H<sub>3</sub>)<sub>2</sub>PH (1.50 g; 3.27 mmol; prepared as described in: Casey, C. P. et al., J. Am. Chem. Soc. (1997), 119, 11817) in THF (30 mL) was cooled to -78 °C and treated with a 1.6 M solution of n-BuLi in hexanes (2.06 mL; 3.30 mmol) to produce a deep-purple reaction mixture. To the latter was added, at stirring, 1,1-

bis(trifluoromethyl)ethylene oxide (0.59 g; 0.453 mL; 3.27 mmol) and the mixture was allowed to warm to room temperature. After stirring at room temperature overnight, the solution was treated with 0.3 mL of trifluoroacetic acid and evaporated to dryness. Flash-chromatography (silica gel, methylene chloride - hexanes 50:50 by volume) of the residue, followed by vacuum sublimation produced  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$  (1.52 g; 73%; slightly contaminated with the corresponding phosphine oxide). Anal. Calcd for  $\text{C}_{20}\text{H}_9\text{F}_{18}\text{OP}$ , %: C, 37.6; H, 1.4. Found, %: C, 37.5; H, 1.4.  $^1\text{H}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 8.0 (m, 6H, arom. H); 3.9 (br. s.; 1H, OH); 2.9 (s, 2H,  $\text{CH}_2$ ).  $^{19}\text{F}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -63.9 (s, 12F,  $(\text{CF}_3)_2\text{C}_6\text{H}_3$ ); -77.8 (d,  $J_{\text{F-P}} = 19.4$  Hz, 6F,  $(\text{CF}_3)_2\text{COH}$ ).  $^{31}\text{P}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -22.1 (septet,  $J_{\text{P-F}} = 19.4$  Hz).

#### Method b:

Under nitrogen, to a stirring solution of 1,1-bis(trifluoromethyl)-2-bromoethanol (0.91 g) in dry ether (20 mL) cooled to -78 °C, was added drop-wise 1.6 M n-BuLi in hexanes (Aldrich; 4.35 mL). After 1 h at -78 °C,  $(3,5-(\text{CF}_3)_2\text{C}_6\text{H}_3)_2\text{PCl}$  (1.63 g; prepared as described in: Casalnuovo et al., US Patent 5175335) was added drop-wise, at vigorous stirring, to the resulting solution of the dilithiated derivative. After stirring for 2 h at -78 °C, the mixture was allowed to warm slowly to room temperature and then stirred at room temperature overnight. The solvents were removed under vacuum. Dichloromethane (5 mL) and trifluoroacetic acid (0.26 mL) were added to the residue. Flash-chromatography (silica gel, dichloromethane) of the mixture produced solid  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$  (1.32 g; 62%) which was found to be identical to the material synthesized according to method b.

#### EXAMPLE 4

This example illustrates the preparation of the phosphinoalkanol precursor compound,  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$ , where  $\text{Ar} = 4\text{-CF}_3\text{C}_6\text{H}_4$  (PO-3H).

Under nitrogen, to a stirring solution of 1,1-bis(trifluoromethyl)-2-bromoethanol (2.28 g) in dry ether (46 mL) cooled to -78 °C, was added drop-wise 1.6 M n-BuLi in hexanes (Aldrich; 10.93 mL). After 1 h at -78 °C,  $(4\text{-CF}_3\text{C}_6\text{H}_4)_2\text{PCl}$  (3.28 g; prepared as described in: Casalnuovo et al., J. Am. Chem. Soc., 1994, 116, 9869) was added drop-wise, at vigorous stirring, to the resulting solution of the dilithiated derivative. After stirring for 2 h at -78 °C, the mixture was allowed to warm slowly to room temperature and then stirred at room temperature overnight. The solvents

were removed under vacuum. Dichloromethane (7 mL) and trifluoroacetic acid (0.64 mL) were added to the residue. Flash-chromatography (silica gel, dichloromethane) of the mixture, followed by solvent evaporation and vacuum-drying produced  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$  (3.36 g; 81%) as a slightly yellow oil. ). Anal. Calcd for  $\text{C}_{18}\text{H}_{11}\text{F}_{12}\text{OP}$ , %: C, 43.0; H, 2.2. Found, %: C, 42.8; H, 2.2.  $^1\text{H}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 7.7 (m, 8H, arom. H); 3.6 (br. s.; 1H, OH); 2.9 (s, 2H,  $\text{CH}_2$ ).  $^{19}\text{F}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -63.5 (s, 6F,  $\text{CF}_3\text{C}_6\text{H}_4$ ); -77.6 (d,  $J_{\text{F-P}} = 18.6$  Hz, 6F,  $(\text{CF}_3)_2\text{COH}$ ).  $^{31}\text{P}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -27.1 (septet,  $J_{\text{P-F}} = 18.6$  Hz).

10

#### EXAMPLE 5

This example illustrates the preparation of the phosphinoalkanol precursor compound,  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$ , where  $\text{Ar} = \text{C}_6\text{F}_5$  (PO-4H).

Under nitrogen, to a stirring solution of 1,1-bis(trifluoromethyl)-2-bromoethanol (3.43 g) in dry ether (70 mL) cooled to -78 °C, was added drop-wise 1.6 M n-BuLi in hexanes (Aldrich; 16.43 mL). After 30 min at -78 °C,  $(\text{C}_6\text{F}_5)_2\text{PCl}$  (5.0 g; prepared as described in: RajanBabu et al., J. Org. Chem., 1999, 64, 3429) was added drop-wise, at vigorous stirring, to the resulting solution of the dilithiated derivative. After stirring for 5.5 h at -78 °C, the mixture was allowed to warm slowly to room temperature and then stirred at room temperature overnight. The solvents were removed under vacuum. Dichloromethane (10 mL) and trifluoroacetic acid (0.96 mL) were added to the residue. Flash-chromatography (silica gel, dichloromethane) of the mixture, followed by solvent evaporation and vacuum-drying produced  $\text{Ar}_2\text{PCH}_2\text{C}(\text{OH})(\text{CF}_3)_2$  (1.58 g; 23%) as a white solid. Anal. Calcd for  $\text{C}_{16}\text{H}_3\text{F}_{16}\text{OP}$ , %: C, 35.2; H, 0.55. Found, %: C, 35.1; H, 0.05.  $^1\text{H}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 3.3 (s, 2H,  $\text{CH}_2$ ); 3.6 (br. s.; 1H, OH).  $^{19}\text{F}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -77.8 (d,  $J_{\text{F-P}} = 20.5$  Hz, 6F,  $\text{CF}_3$ ); -130.6 (m, 4F, o- $\text{C}_6\text{F}_5$ ); -150.0 (t,  $J_{\text{F-F}} = 20$  Hz; 2F, p- $\text{C}_6\text{F}_5$ ); -161.0 (m, 4F, m- $\text{C}_6\text{F}_5$ ).  $^{31}\text{P}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -57.6 (m).

20  
25  
30

#### EXAMPLE 6

This example illustrates the formation of dichloro-bridged dinuclear bis-cyclometallated Ir complexes.

The Ir complexes were prepared by the reaction between  $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$  and the corresponding 2-arylpyridine in aqueous 2-ethoxyethanol. The method is similar to the literatures procedure for 2-phenylpyridine (Sprouse, S.; King, K. A.; Spellane, P. J.; Watts, R. J., J. Am. Chem. Soc., 1984, 106, 6647-53; Garces, F. O.; King, K. A.; Watts, R. J., Inorg. Chem., 1988, 27, 3464-71.). A mixture of  $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ , a 2-

35



arylpyridine (2.2 - 2.8 equivalents per Ir), 2-ethoxyethanol (ca. 30 mL per 1 g of  $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ ), and water (ca. 5 mL per 30 mL of 2-ethoxyethanol) was vigorously stirred under reflux ( $\text{N}_2$ ) for 4-10 hours. After cooling to room temperature, conc. HCl (3 mL per 1 g  $\text{IrCl}_3 \cdot n\text{H}_2\text{O}$ ) was added, and the mixture was stirred for 30 min. The mixture was diluted with water, stirred for 1-2 hours, and filtered. The solid product was washed with water, methanol, and dried under vacuum. The yields ranged from 65 to 99%.

#### EXAMPLE 7

This example illustrates the formation of Ir complexes of the invention having the Formula I.

#### Dicyclometalated Arylpyridine Iridium (III) Mononuclear Complexes containing Phosphinoalkanol Ligands.

The general procedure was to combine a dichloro-bridged dinuclear bis-cyclometallated Ir complex from Example 6, a phosphinoalkanol compound (1.1-1.5 equivs per Ir), 1,2-dichloroethane (DCE; 3-12 mL), and 10% aqueous NaOH (2-10-fold excess) and stir under reflux ( $\text{N}_2$ ) until all solids dissolved and then for additional 0.5-1.5 hours. The products were isolated and purified in air. The organic layer was separated, filtered through a short silica gel plug, and reduced in volume to 0.5-2 mL. Treatment of the residue with hexanes resulted in crystallization (1-3 h) of the desired product which was separated, washed with hexanes, and dried under vacuum. X-ray analysis of three complexes (2-b, 2-g, 2-j, and 2-u) indicated trans arrangement of the nitrogen atoms.  $^{31}\text{P}$  NMR =  $^{31}\text{P}\{-^1\text{H}\}$  NMR.

#### Compound 2-a (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ab from Example 1 (150 mg), phosphinoalkanol PO-1H from Example 2 (100 mg), DCE (3 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $\text{N}_2$ ) for 1 h. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 1-2 mL and treated with hexanes (10 mL; portionwise). The lemon-yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.22 g (97%). Anal. Calcd for  $\text{C}_{40}\text{H}_{28}\text{F}_{10}\text{N}_2\text{IrOP} \cdot \text{C}_2\text{H}_4\text{Cl}_2$ , %: C, 47.4; H, 3.0; N, 2.6. Found, %: C, 47.5; H, 3.1; N, 2.5.  $^1\text{H}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 2.5 (s, 3H,  $\text{CH}_3$ ); 2.51

(s, 3H, CH<sub>3</sub>); 3.0 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 9.1 Hz, 1H, CH<sub>2</sub>); 3.6 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 3.8 (s, solvent C<sub>2</sub>H<sub>4</sub>Cl<sub>2</sub>); 5.5 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.5 (m, 2H, arom H); 6.65 (m, 1H, arom H); 6.7 (m, 3H, arom H); 7.0 (m, 2H, arom H); 7.1 (m, 1H, arom H); 7.4 (m, 3H, arom H); 7.6 (m, 3H, arom H); 8.0 (s, 1H, arom H); 8.2 (s, 1H, arom H); 8.3 (d, 1H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -75.1 (m, 3F, CF<sub>3</sub>); -78.8 (m, 3F, CF<sub>3</sub>); -109.2 (m, 1F, arom F); -109.9 (m, 1F, arom F); -110.4 (m, 1F, arom F); -111.0 (m, 1F, arom F). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 10.2 (s).

10

#### Compound 2-b (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ab from Example 1 (200 mg), phosphinoalkanol PO-2H from Example 3 (270 mg), DCE (6 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 25 min. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 1-2 mL and treated with hexanes (10 mL; portionwise). The lemon-yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.38 g (97%). Anal. Calcd for C<sub>44</sub>H<sub>24</sub>F<sub>22</sub>N<sub>2</sub>IrOP, %: C, 42.7; H, 1.9; N, 2.3. Found, %: C, 42.5; H, 1.9; N, 2.3. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.5 (s, 3H, CH<sub>3</sub>); 2.51 (s, 3H, CH<sub>3</sub>); 3.1 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 8.3 Hz, 1H, CH<sub>2</sub>); 3.8 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.5 Hz, 1H, CH<sub>2</sub>); 5.4 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.6 (m, 2H, arom H); 6.7 (m, 1H, arom H); 6.9 (m, 1H, arom H); 7.25 (m, 2H, arom H); 7.7 (s, 1H, arom H); 8.1 (m, 5H, arom H); 8.25 (m, 1H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -63.8 (s, 6F, arom CF<sub>3</sub>); -64.1 (s, 6F, arom CF<sub>3</sub>); -75.0 (m, 3F, HOCCF<sub>3</sub>); -79.1 (m, 3F, HOCCF<sub>3</sub>); -107.6 (m, 1F, arom F); -108.1 (m, 1F, arom F); -109.7 (m, 2F, arom F). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 14.6 (s). The structure was confirmed by X-ray analysis.

35

#### Compound 2-c (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ah from Example 1 (200 mg), phosphinoalkanol PO-1H from Example 2 (150 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 0.5 h. The yellow

organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 1-2 mL and treated with hexanes (10 mL; portionwise). The lemon-yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.29 g (94%). Anal. Calcd for  $C_{38}H_{24}F_{10}N_2IrOP$ , %: C, 48.7; H, 2.6; N, 3.0. Found, %: C, 49.1; H, 2.7; N, 2.8.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 3.05 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 9.1$  Hz, 1H,  $CH_2$ ); 3.6 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 12.1$  Hz, 1H,  $CH_2$ ); 5.4 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.5 (m, 2H, arom H); 7.0 (m, 8H, arom H); 7.5 (m, 6H, arom H); 7.7 (t, 1H, arom H); 7.7.8 (t, 1H, arom H); 8.15 (d, 1H, arom H); 8.3 (dd, 1H, arom H); 8.5 (d, 1H, arom H); 8.9 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -75.0 (m, 3F,  $CF_3$ ); -78.9 (m, 3F,  $CF_3$ ); -108.6 (m, 1F, arom F); -109.2 (m, 1F, arom F); -110.3 (m, 1F, arom F); -110.9 (m, 1F, arom F).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 10.4 (s).

#### Compound 2-d (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ah from Example 1 (150 mg), phosphinoalkanol PO-2H from Example 3 (190 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $N_2$ ) for 20 min. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 1-2 mL and treated with hexanes (5 mL). The lemon-yellow needle-shaped crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.255 g (85%). Anal. Calcd for  $C_{42}H_{20}F_{22}N_2IrOP$ , %: C, 41.7; H, 1.7; N, 2.3. Found, %: C, 41.7; H, 1.2; N, 2.4.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 3.1 (dd,  $J_{H-H} = 16.6$  Hz,  $J_{H-P} = 8.3$  Hz, 1H,  $CH_2$ ); 3.8 (dd,  $J_{H-H} = 16.6$  Hz,  $J_{H-P} = 12.4$  Hz, 1H,  $CH_2$ ); 5.45 (m, 1H, arom H); 6.15 (m, 1H, arom H); 6.6 (m, 2H, arom H); 6.9 (t, 1H, arom H); 7.0 (t, 1H, arom H); 7.25 (d, 2H, arom H); 7.7 (m, 2H, arom H); 7.9 (t, 1H, arom H); 8.1 (m, 2H, arom H); 8.2 (d, 1H, arom H); 8.25 (d, 1H, arom H); 8.4 (dd, 2H, arom H); 8.9 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -63.7 (s, 6F, arom  $CF_3$ ); -64.0 (s, 6F, arom  $CF_3$ ); -75.0 (m, 3F,  $HOCCF_3$ ); -79.1 (m, 3F,  $HOCCF_3$ ); -106.9 (m, 1F, arom F); -107.4 (m, 1F, arom F); -109.5 (m, 2F, arom F).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 14.6 (s).

Compound 2-e (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ag from Example 1 (110 mg),  
 5 phosphinoalkanol PO-1H from Example 2 (85 mg), DCE (3 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 0.5 h. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were  
 10 reduced in volume to ca. 0.5 mL and treated with hexanes (5 mL; portionwise). The lemon-yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.17 g (99%). Anal. Calcd for C<sub>40</sub>H<sub>26</sub>F<sub>12</sub>N<sub>2</sub>IrOP·1/2C<sub>2</sub>H<sub>4</sub>Cl<sub>2</sub>, %: C, 46.8; H, 2.7; N, 2.7. Found, %: C, 46.4; H, 2.7; N, 2.4. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 3.05 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 8.7 Hz, 1H, CH<sub>2</sub>); 3.65 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 11.7 Hz, 1H, CH<sub>2</sub>); 3.8 (s, solvent C<sub>2</sub>H<sub>4</sub>Cl<sub>2</sub>); 6.1 (m, 1H, arom H); 7.0 (m, 10H, arom H); 7.4 (m, 3H, arom H); 7.5 (m, 2H, arom H); 7.7 (m, 1H, arom H); 7.9 (m, 5H, arom H); 8.5 (d, 1H, arom H); 9.0 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -62.4 (s, 3F, arom CF<sub>3</sub>); -62.7 (s, 3F, arom CF<sub>3</sub>); -75.1 (m, 3F, CF<sub>3</sub>); -79.0 (m, 3F, CF<sub>3</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 10.6 (s).

Compound 2-f (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ac from Example 1 (350 mg),  
 25 phosphinoalkanol PO-1H from Example 2 (205 mg), DCE (4 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 30 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a short silica gel plug, then reduced in volume to ca. 1 mL and treated with hexanes (10 mL). After 1 h the  
 30 pale greenish-yellow crystals (blue-photoluminescent) were separated, washed with hexanes, and dried under vacuum. Yield: 0.44 g (90%). Anal. Calcd for C<sub>44</sub>H<sub>28</sub>F<sub>18</sub>N<sub>2</sub>IrOP, %: C, 45.3; H, 2.4; N, 2.4. Found, %: C, 45.0; H, 2.2; N, 2.3. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.35 (s, 3H, CH<sub>3</sub>); 2.5 (s, 3H, CH<sub>3</sub>); 2.9 (dd, J<sub>H-H</sub> = 16.5 Hz, J<sub>H-P</sub> = 10.2 Hz, 1H, CH<sub>2</sub>); 3.3 (dd, J<sub>H-H</sub> = 16.5 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 6.5 (d, 1H, arom H); 6.7 (m, 2H, arom H); 6.8 (d, 1H, arom H); 7.0 (m, 2H, arom H); 7.2 (m, 4H, arom H); 7.4 (m, 2H, arom H); 7.5 (m, 1H, arom H); 7.6 (s, 1H, arom H); 7.75 (s, 1H, arom H); 7.9 (d, 2H, arom H); 8.2 (m, 2H, arom H); 8.65 (d, 1H, arom H). <sup>19</sup>F

NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -58.2 (s, 3F, arom  $\text{CF}_3$ ); -59.8 (s, 3F, arom  $\text{CF}_3$ ); -62.7 (s, 3F, arom  $\text{CF}_3$ ); -63.0 (s, 3F, arom  $\text{CF}_3$ ); -73.5 (m, 3F,  $\text{HOCCF}_3$ ); -79.2 (m, 3F,  $\text{HOCCF}_3$ ).  $^{31}\text{P}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 11.4 (s).

5 Compound 2-g (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ac from Example 1 (200 mg), phosphinoalkanol PO-2H from Example 3 (190 mg), DCE (5 mL), and 10% NaOH (0.7 mL) was vigorously stirred under reflux ( $\text{N}_2$ ) for 15 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then reduced in volume to ca. 2-3 mL and treated with hexanes (10 mL). The pale-yellow crystals (blue-photoluminescent) were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.30 g (87%). Anal. Calcd for  $\text{C}_{48}\text{H}_{24}\text{F}_{30}\text{N}_2\text{IrOP}$ , %: C, 40.1; H, 1.7; N, 2.0. Found, %: C, 40.1; H, 1.2; N, 2.1.  $^1\text{H}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 2.35 (s, 3H,  $\text{CH}_3$ ); 2.55 (s, 3H,  $\text{CH}_3$ ); 2.95 (dd,  $J_{\text{H-H}} = 16.6$  Hz,  $J_{\text{H-P}} = 9.5$  Hz, 1H,  $\text{CH}_2$ ); 3.6 (dd,  $J_{\text{H-H}} = 16.6$  Hz,  $J_{\text{H-P}} = 12.5$  Hz, 1H,  $\text{CH}_2$ ); 6.6 (d, 1H, arom H); 6.8 (d, 1H, arom H); 7.2 (d, 2H, arom H); 7.3 (s, 1H, arom H); 7.6 (m, 3H, arom H); 7.8 (s, 1H, arom H); 7.9 (m, 3H, arom H); 8.1 (s, 2H, arom H); 8.2 (s, 1H, arom H); 8.6 (d, 1H, arom H).  $^{19}\text{F}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : -58.3 (s, 3F, arom  $\text{CF}_3$ ); -60.1 (s, 3F, arom  $\text{CF}_3$ ); -63.1 (s, 3F, arom  $\text{CF}_3$ ); -63.6 (s, 3F, arom  $\text{CF}_3$ ); -63.9 (s, 6F, arom  $\text{CF}_3$ ); -64.2 (s, 6F, arom  $\text{CF}_3$ ); -73.0 (m, 3F,  $\text{HOCCF}_3$ ); -79.7 (m, 3F,  $\text{HOCCF}_3$ ).  $^{31}\text{P}$  NMR ( $\text{CD}_2\text{Cl}_2$ , 20 °C),  $\delta$ : 13.7 (s). The structure was confirmed by X-ray analysis.

Compound 2-h (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ad from Example 1 (430 mg), phosphinoalkanol PO-1H from Example 2 (310 mg), DCE (10 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $\text{N}_2$ ) for 1 h. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 1-2 mL and treated with hexanes (10 mL; portionwise). The lemon-yellow crystals were separated, recrystallized from boiling toluene, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.45 g (65%). Anal. Calcd for

$C_{47}H_{36}F_{10}N_2IrOP$  (1:1 toluene solvate), %: C, 53.4; H, 3.4; N, 2.7. Found, %: C, 53.2; H, 3.1; N, 2.7.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 1.9 (s, 3H,  $CH_3$ ); 2.2 (s, 3H,  $CH_3$ ); 2.4 (s, solvent toluene); 3.0 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 9.0$  Hz, 1H,  $CH_2$ ); 3.6 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 11.7$  Hz, 1H,  $CH_2$ ); 5.5 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.5 (m, 2H, arom H); 6.7 (m, 2H, arom H); 7.0 (m, 2H, arom H); 7.2 (m, 4H, arom H); 7.5 (m, 8H, arom H); 8.05 (d, 1H, arom H); 8.2 (dd, 1H, arom H); 8.3 (s, 1H, arom H); 8.85 (s, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -75.0 (m, 3F,  $CF_3$ ); -79.0 (m, 3F,  $CF_3$ ); -109.5 (m, 1F, arom F); -110.2 (m, 1F, arom F); -111.4 (m, 1F, arom F); -111.8 (m, 1F, arom F).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 11.2 (s).

#### Compound 2-i (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ad from Example 1 (200 mg), phosphinoalkanol PO-2H from Example 3 (240 mg), DCE (6 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $N_2$ ) for 1 h 10 min. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 2 mL and treated with hexanes (10 mL). After 1 hour, the pale-yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.31 g (80%). Anal. Calcd for  $C_{44}H_{24}F_{22}N_2IrOP$ , %: C, 42.7; H, 1.9; N, 2.3. Found, %: C, 42.5; H, 1.4; N, 2.4.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 1.9 (s, 3H,  $CH_3$ ); 2.2 (s, 3H,  $CH_3$ ); 3.1 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 8.7$  Hz, 1H,  $CH_2$ ); 3.75 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 12.5$  Hz, 1H,  $CH_2$ ); 5.4 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.6 (m, 2H, arom H); 7.2 (d, 2H, arom H); 7.5 (d, 1H, arom H); 7.7 (m, 2H, arom H); 8.1 (m, 5H, arom H); 8.3 (dd, 1H, arom H); 8.7 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -63.8 (s, 6F, arom  $CF_3$ ); -63.9 (s, 6F, arom  $CF_3$ ); -75.0 (m, 3F,  $HOCCF_3$ ); -79.1 (m, 3F,  $HOCCF_3$ ); -107.9 (m, 1F, arom F); -108.3 (m, 1F, arom F); -110.3 (m, 1F, arom F); -110.6 (m, 1F, arom F).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 14.6 (s).

#### Compound 2-j (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-k (340 mg) from Example 1, phosphinoalkanol PO-1H from Example 2 (220 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $N_2$ ) for 20 min. The

yellow organic layer (green photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to ca. 1 mL and treated with hexanes (10 mL). The yellow oil solidified upon trituration. The solid was recrystallized from dichloromethane-hexanes, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.45 g (90%). The structure was confirmed by X-ray analysis (1:1 hydrate with H<sub>2</sub>O hydrogen-bonded to the O atom of the complex). <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 3.0 (dd, J<sub>H-H</sub> = 16.6 Hz, J<sub>H-P</sub> = 9.1 Hz, 1H, CH<sub>2</sub>); 3.6 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 3.8 (s, solvent C<sub>2</sub>H<sub>4</sub>Cl<sub>2</sub>), 5.5 (m, 1H, arom H); 5.6 (m, 1H, arom H); 6.4 (m, 1H, arom H); 6.7 (m, 4H, arom H); 7.0 (m, 2H, arom H); 7.1 (m, 1H, arom H); 7.4 (m, 3H, arom H); 7.5 (m, 2H, arom H); 7.7 (m, 4H, arom H); 8.0 (m, 2H, arom H); 8.8 (s, 1H, arom H); 9.2 (s, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -63.3 (br m, 3F, arom CF<sub>3</sub>); -63.5 (s, 3F, arom CF<sub>3</sub>); -75.5 (m, 3F, CF<sub>3</sub>); -78.9 (m, 3F, CF<sub>3</sub>); -108.0 (m, 1F, arom F); -108.5 (m, 1F, arom F). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 12.2 (s).

#### Compound 2-k (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ai from Example 1 (300 mg), phosphinoalkanol PO-1H from Example 2 (215 mg), DCE (5 mL), and 10% NaOH (2 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 2 h. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were evaporated to dryness and treated with hexanes (10 mL). The yellow oil (blue-photoluminescent) dissolved upon heating the mixture after a few hours at room temperature yellow solid formed. The product was washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.22 g (50%). Anal. Calcd for C<sub>46</sub>H<sub>40</sub>F<sub>10</sub>N<sub>2</sub>IrOP, %: C, 52.6; H, 3.8; N, 2.7. Found, %: C, 53.5; H, 3.8; N, 2.8. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.5 (s, 3H, CH<sub>3</sub>); 2.51 (s, 3H, CH<sub>3</sub>); 3.0 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 9.1 Hz, 1H, CH<sub>2</sub>); 3.6 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 3.8 (s, solvent C<sub>2</sub>H<sub>4</sub>Cl<sub>2</sub>), 5.5 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.5 (m, 2H, arom H); 6.65 (m, 1H, arom H); 6.7 (m, 3H, arom H); 7.0 (m, 2H, arom H); 7.1 (m, 1H, arom H); 7.4 (m, 3H, arom H); 7.6 (m, 3H, arom H); 8.0 (s, 1H, arom H); 8.2 (s, 1H, arom H); 8.3 (d, 1H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -

75.0 (m, 3F, CF<sub>3</sub>); -79.0 (m, 3F, CF<sub>3</sub>); -109.3 (m, 1F, arom F); -110.0 (m, 1F, arom F); -110.7 (m, 1F, arom F); -111.3 (m, 1F, arom F). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 10.2 (s).

5 Compound 2-l (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-aj from Example 1 (217 mg), phosphinoalkanol PO-1H from Example 2 (100 mg), DCE (4 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 10 min. The yellow organic layer (blue-green photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were evaporated to ca. 1 mL, treated with hexanes (5 mL), and left at room temperature overnight. The yellow crystals (blue-green-photoluminescent) were washed with hexanes (3 x 2 mL), and dried under vacuum. Yield: 0.195 g (66%). Anal. Calcd for C<sub>50</sub>H<sub>40</sub>F<sub>18</sub>N<sub>2</sub>IrOP, %: C, 48.0; H, 3.2; N, 2.2. Found, %: C, 47.6; H, 3.0; N, 2.1. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 1.3 (s, 9H, t-Bu); 1.4 (s, 9H, CH<sub>3</sub>); 2.9 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 10.2 Hz, 1H, CH<sub>2</sub>); 3.3 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 6.6 (dd, 1H, arom H); 6.8 (m, 2H, arom H); 7.0 (m, 3H, arom H); 7.2 (m, 3H, arom H); 7.4 (m, 4H, arom H); 7.6 (s, 1H, arom H); 7.8 (s, 1H, arom H); 8.0 (m, 2H, arom H); 8.2 (s, 1H, arom H); 8.3 (m, 1H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -58.4 (s, 3F, arom CF<sub>3</sub>); -59.8 (s, 3F, arom CF<sub>3</sub>); -62.4 (s, 3F, arom CF<sub>3</sub>); -62.6 (s, 3F, arom CF<sub>3</sub>); -73.2 (m, 3F, aliph CF<sub>3</sub>); -79.2 (m, 3F, aliph CF<sub>3</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 9.8 (s).

Compound 2-m (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ad from Example 1 (150 mg), phosphinoalkanol PO-3H from Example 4 (140 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 1 h 30 min. The yellow organic layer (blue photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to 2 mL and treated with hexanes (10 mL). The pale-yellow crystals were recrystallized from dichloromethane-hexanes, washed with hexanes (3 x 5 mL), and dried



under vacuum. Yield: 0.23 g (88%). Anal. Calcd for  $C_{42}H_{26}F_{16}N_2IrOP$ , %: C, 45.8; H, 2.4; N, 2.5. Found, %: C, 45.2; H, 2.2; N, 2.4.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 1.9 (s, 3H,  $CH_3$ ); 2.2 (s, 3H,  $CH_3$ ); 3.1 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 9.1$  Hz, 1H,  $CH_2$ ); 3.6 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 12.1$  Hz, 1H,  $CH_2$ ); 5.5 (m, 1H, arom H); 6.1 (m, 1H, arom H); 6.5 (m, 2H, arom H); 6.9 (m, 2H, arom H); 7.3 (d, 2H, arom H); 7.7 (m, 6H, arom H); 8.0 (m, 1H, arom H); 8.2 (m, 1H, arom H); 8.8 (s, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -63.9 (s, 3F, arom  $CF_3$ ); -64.0 (s, 3F, arom  $CF_3$ ); -75.0 (m, 3F,  $HOCCF_3$ ); -79.0 (m, 3F,  $HOCCF_3$ ); -108.9 (m, 1F, arom F); -109.2 (m, 1F, arom F); -111.0 (m, 1F, arom F); -111.1 (m, 1F, arom F).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 13.1 (s).

#### Compound 2-n (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ab from Example 1 (60 mg), phosphinoalkanol PO-3H from Example 4 (60 mg), DCE (3 mL), and 10% NaOH (0.5 mL) was vigorously stirred under reflux ( $N_2$ ) for 30 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then reduced in volume to ca. 0.5 mL and treated with hexanes (4 mL). The pale-yellow crystals (blue-photoluminescent) were separated, washed with hexanes (3 x 1 mL), and dried under vacuum. Yield: 0.085 g (82%). Anal. Calcd for  $C_{42}H_{26}F_{16}N_2IrOP$ , %: C, 45.8; H, 2.4; N, 2.5. Found, %: C, 46.4; H, 2.2; N, 2.3.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 2.35 (s, 3H,  $CH_3$ ); 2.55 (s, 3H,  $CH_3$ ); 2.95 (dd,  $J_{H-H} = 16.6$  Hz,  $J_{H-P} = 9.5$  Hz, 1H,  $CH_2$ ); 3.6 (dd,  $J_{H-H} = 16.6$  Hz,  $J_{H-P} = 12.5$  Hz, 1H,  $CH_2$ ); 6.6 (d, 1H, arom H); 6.8 (d, 1H, arom H); 7.2 (d, 2H, arom H); 7.3 (s, 1H, arom H); 7.6 (m, 3H, arom H); 7.8 (s, 1H, arom H); 7.9 (m, 3H, arom H); 8.1 (s, 2H, arom H); 8.2 (s, 1H, arom H); 8.6 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -63.9 (s, 3F, arom  $CF_3$ ); -64.0 (s, 3F, arom  $CF_3$ ); -75.1 (m, 3F,  $HOCCF_3$ ); -78.8 (m, 3F,  $HOCCF_3$ );  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 12.7 (s).

#### Compound 2-o (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-al from Example 1 (170 mg), phosphinoalkanol PO-1H from Example 2 (140 mg), DCE (3 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $N_2$ ) for 20 min. The yellow organic layer (green photoluminescent) was separated and filtered

through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to ca. 0.5 mL and treated with hexanes (10 mL, portionwise). The yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.25 g (92%). Anal. Calcd for  $C_{44}H_{36}F_6N_2IrO_5P \cdot 1/2C_2H_4Cl$ , %: C, 51.0; H, 3.6; N, 2.6. Found, %: C, 50.7; H, 3.7; N, 2.7.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 3.0 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 8.7$  Hz, 1H,  $CH_2$ ); 3.4 (s, 3H,  $CH_3O$ ); 3.55 (s, 3H,  $CH_3O$ ); 3.6 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 11.3$  Hz, 1H,  $CH_2$ ); 3.95 (s, 3H,  $CH_3O$ ); 4.0 (s, 3H,  $CH_3O$ ); 5.05 (m, 1H, arom H); 5.7 (m, 1H, arom H); 6.2 (m, 2H, arom H); 6.6 (m, 1H, arom H); 6.8 (m, 3H, arom H); 6.95 (m, 2H, arom H); 7.05 (m, 1H, arom H); 7.4 (m, 3H, arom H); 7.6 (m, 4H, arom H); 8.4 (d, 1H, arom H); 8.6 (d, 1H, arom H); 8.7 (d, 1H, arom H); 8.9 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -75.1 (m, 3F,  $HOCCF_3$ ); -79.0 (m, 3F,  $HOCCF_3$ ).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 8.5 (s).

#### Compound 2-p (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-al from Example 1 (110 mg), phosphinoalkanol PO-2H from Example 3 (125 mg), DCE (3 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux ( $N_2$ ) for 20 min. The yellow organic layer (bluish-green photoluminescent) was separated and filtered through a short silica plug. The aqueous layer was extracted with dichloromethane and passed through the same plug. The combined organic solutions were reduced in volume to ca. 0.5 mL and treated with hexanes (4 mL). The yellow crystals were separated, washed with hexanes (3 x 5 mL), and dried under vacuum. Yield: 0.18 g (85%). Anal. Calcd for  $C_{46}H_{32}F_{18}N_2IrO_5P$ , %: C, 43.9; H, 2.6; N, 2.2. Found, %: C, 43.8; H, 2.1; N, 2.4.  $^1H$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 3.1 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 9.1$  Hz, 1H,  $CH_2$ ); 3.4 (s, 3H,  $CH_3O$ ); 3.55 (s, 3H,  $CH_3O$ ); 3.7 (dd,  $J_{H-H} = 16.2$  Hz,  $J_{H-P} = 12.1$  Hz, 1H,  $CH_2$ ); 3.95 (s, 3H,  $CH_3O$ ); 4.0 (s, 3H,  $CH_3O$ ); 5.15 (m, 1H, arom H); 5.75 (m, 1H, arom H); 6.2 (m, 2H, arom H); 6.7 (m, 1H, arom H); 6.8 (m, 1H, arom H); 7.25 (d, 2H, arom H); 7.5 (t, 1H, arom H); 7.65 (s, 1H, arom H); 7.7 (t, 1H, arom H); 8.0 (s, 1H, arom H); 8.1 (d, 2H, arom H); 8.25 (d, 1H, arom H); 8.45 (d, 1H, arom H); 8.75 (d, 1H, arom H); 8.85 (d, 1H, arom H).  $^{19}F$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : -63.7 (s, 6F, arom  $CF_3$ ); -64.0 (s, 6F, arom  $CF_3$ ); -75.1 (m, 3F,  $HOCCF_3$ ); -78.9 (m, 3F,  $HOCCF_3$ ).  $^{31}P$  NMR ( $CD_2Cl_2$ , 20 °C),  $\delta$ : 14.6 (s).

Compound 2-q (Table 2)

- A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ae from Example 1 (520 mg),  
 5 phosphinoalkanol PO-1H from Example 2 (340 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 30 min. The reaction mixture was extracted with toluene and then dichloromethane and the combined organic extracts were filtered through a short silica gel plug, then reduced in volume to ca. 3 mL and treated with hexanes (20 mL).  
 10 After 1 h the yellow crystals (blue-green photoluminescent) were separated, washed with hexanes, and dried under vacuum. Yield: 0.755 g (92%). Anal. Calcd for C<sub>45.5</sub>H<sub>34</sub>F<sub>12</sub>N<sub>2</sub>IrOP (crystallized with 1/2 molecule of toluene), %: C, 50.8; H, 3.2; N, 2.6. Found, %: C, 50.8; H, 3.1; N, 2.6. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.55 (s, 3H, CH<sub>3</sub>); 2.6 (s, 3H, CH<sub>3</sub>); 3.0 (dd, J<sub>H-H</sub> =  
 15 16.2 Hz, J<sub>H-P</sub> = 8.7 Hz, 1H, CH<sub>2</sub>); 3.6 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 11.7 Hz, 1H, CH<sub>2</sub>); 6.1 (m, 1H, arom H); 6.7 (m, 4H, arom H); 6.9 (m, 1H, arom H); 7.0 (m, 2H, arom H); 7.1 (m, 3H, arom H); 7.2 (m, 1H, arom H); 7.5 (m, 3H, arom H); 7.6 (m, 2H, arom H); 7.7 (s, 1H, arom H); 7.8 (s, 1H, arom H); 7.9 (s, 1H, arom H); 7.95 (s, 1H, arom H); 8.3 (d, 1H, arom H); 8.75 (d,  
 20 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -62.2 (s, 3F, arom CF<sub>3</sub>); -62.8 (s, 3F, arom CF<sub>3</sub>); -75.2 (m, 3F, HOCCF<sub>3</sub>); -78.9 (m, 3F, HOCCF<sub>3</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 10.3 (s).

Compound 2-r (Table 2)

- 25 A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ae from Example 1 (200 mg), phosphinoalkanol PO-2H from Example 3 (230 mg), DCE (5 mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 10 min. The reaction mixture was extracted with dichloromethane and the combined  
 30 organic extracts were filtered through a silica gel column, then reduced in volume to ca. 1-2 mL and treated with hexanes (7 mL). After 3 hours the pale-yellow crystals (blue-photoluminescent) were separated, washed with hexanes (3 x 3 mL), and dried under vacuum. Yield: 0.34 g (90%). Anal. Calcd for C<sub>46</sub>H<sub>26</sub>F<sub>24</sub>N<sub>2</sub>IrOP, %: C, 42.4; H, 2.0; N, 2.2. Found, %: C, 42.2;  
 35 H, 1.4; N, 2.3. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.3 (s, 3H, CH<sub>3</sub>); 2.6 (s, 3H, CH<sub>3</sub>); 3.1 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 8.3 Hz, 1H, CH<sub>2</sub>); 3.8 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 6.1 (m, 1H, arom H); 6.7 (m, 2H, arom H); 7.0 (d, 1H, arom H); 7.1 (d, 1H, arom H); 7.2 (m, 3H, arom H); 7.7 (m, 2H,

arom H); 7.9 (m, 3H, arom H); 8.1 (m, 4H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -62.9 (s, 3F, arom CF<sub>3</sub>); -63.0 (s, 3F, arom CF<sub>3</sub>); -63.6 (s, 3F, arom CF<sub>3</sub>); -63.9 (s, 3F, arom CF<sub>3</sub>); -75.1 (m, 3F, HOCCF<sub>3</sub>); -79.1 (m, 3F, HOCCF<sub>3</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 14.6 (s).

5

#### Compound 2-s (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ak from Example 1 (220 mg), phosphinoalkanol PO-1H from Example 2 (140 mg), DCE (4 mL), and 10% NaOH (0.5 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 25 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then reduced in volume to ca. 1 mL and treated with hexanes (8 mL). After 1 hour at room temperature and then 30 min at +5 °C the pale-yellow crystals (green-photoluminescent) were separated, washed with hexanes (3 x 1 mL), and dried under vacuum. Yield: 0.30 g (94%). Anal. Calcd for C<sub>42</sub>H<sub>30</sub>F<sub>12</sub>N<sub>2</sub>IrOP, %: C, 49.0; H, 2.9; N, 2.7. Found, %: C, 49.0; H, 2.8; N, 2.5. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.55 (s, 3H, CH<sub>3</sub>); 2.6 (s, 3H, CH<sub>3</sub>); 3.0 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 8.7 Hz, 1H, CH<sub>2</sub>); 3.6 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 12.1 Hz, 1H, CH<sub>2</sub>); 6.2 (m, 1H, arom H); 6.7 (m, 3H, arom H); 7.0 (m, 4H, arom H); 7.1 (m, 1H, arom H); 7.4 (m, 7H, arom H); 7.7 (m, 4H, arom H); 8.3 (d, 1H, arom H); 8.8 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -63.3 (s, 6F, arom CF<sub>3</sub>); -75.1 (m, 3F, HOCCF<sub>3</sub>); -79.0 (m, 3F, HOCCF<sub>3</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 9.0 (s).

25

#### Compound 2-t (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ac from Example 1 (160 mg), phosphinoalkanol PO-4H from Example 5 (120 mg), DCE (4 mL), and 10% NaOH (0.2 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 10 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then reduced in volume to ca. 1 mL and treated with hexanes (8 mL). The yellow precipitate was recrystallized from dichloromethane (warm) - hexanes, washed with hexanes (3 x 1 mL), and dried under vacuum. Yield: 0.222 g (86%). Anal. Calcd for C<sub>44</sub>H<sub>18</sub>F<sub>28</sub>N<sub>2</sub>IrOP, %: C, 39.3; H, 1.3; N, 2.1. Found, %: C, 39.4; H, 1.2; N, 2.0. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 2.5 (s, 3H, CH<sub>3</sub>); 2.6 (s, 3H, CH<sub>3</sub>); 2.7 (dd, J<sub>H-H</sub> = 17.0 Hz, J<sub>H-P</sub> = 8.7 Hz, 1H, CH<sub>2</sub>); 4.3

(dd,  $J_{H-H} = 17.0$  Hz,  $J_{H-P} = \text{ca. } 17.0$  Hz, 1H, CH<sub>2</sub>); 6.8 (m, 2H, arom H); 7.6 (s, 1H, arom H); 7.65 (s, 1H, arom H); 7.7 (s, 1H, arom H); 7.9 (s, 1H, arom H); 8.0 (s, 1H, arom H); 8.2 (m, 2H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C),  $\delta$ : -57.9 (s, 3F, arom CF<sub>3</sub>); -59.5 (br s, 3F, arom CF<sub>3</sub>); -62.8 (s, 3F, arom CF<sub>3</sub>); -63.0 (s, 3F, arom CF<sub>3</sub>); -74.6 (m, 3F, HOCCF<sub>3</sub>); -78.7 (m, 3F, HOCCF<sub>3</sub>); -124.2 (br s, 2F, C<sub>6</sub>F<sub>5</sub>); ca. -128 (very br s, 2F, C<sub>6</sub>F<sub>5</sub>); -144.5 (m, 1F, C<sub>6</sub>F<sub>5</sub>); -147.7 (m, 1F, C<sub>6</sub>F<sub>5</sub>); -157.7 (br s, 2F, C<sub>6</sub>F<sub>5</sub>); -159.8 (br s, 2F, C<sub>6</sub>F<sub>5</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C),  $\delta$ : -13.4 (br s).

#### 10 Compound 2-u (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with phenylpyridine compound 1-ab from Example 1 (100 mg), phosphinoalkanol PO-4H from Example 5 (98 mg), DCE (4 mL), and 10% NaOH (0.2 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 15 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then evaporated to dryness. The yellow residue was recrystallized from dichloromethane - hexanes, washed with hexanes (3 x 1 mL), and dried under vacuum.

Yield of the product (1:1 dichloromethane solvate): 0.135 g (70%). Anal.

20 Calcd for C<sub>41</sub>H<sub>20</sub>F<sub>20</sub>N<sub>2</sub>IrOPCl<sub>2</sub>, %: C, 40.0; H, 1.6; N, 2.3. Found, %: C, 40.1; H, 1.5; N, 2.2. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C),  $\delta$ : 2.5 (s, 3H, CH<sub>3</sub>); 2.6 (s, 3H, CH<sub>3</sub>); 2.7 (dd,  $J_{H-H} = 17.0$  Hz,  $J_{H-P} = 8.7$  Hz, 1H, CH<sub>2</sub>); 4.3 (dd,  $J_{H-H} = 17.0$  Hz,  $J_{H-P} = \text{ca. } 17.0$  Hz, 1H, CH<sub>2</sub>); 6.8 (m, 2H, arom H); 7.6 (s, 1H, arom H); 7.65 (s, 1H, arom H); 7.7 (s, 1H, arom H); 7.9 (s, 1H, arom H); 8.0 (s, 1H, arom H); 8.2 (m, 2H, arom H); 8.7 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C),  $\delta$ : -76.9 (m, 3F, CF<sub>3</sub>); -78.4 (m, 3F, CF<sub>3</sub>); -108.0 (m, 1F, arom F); -109.7 (m, 1F, arom F); -109.8 (m, 1F, arom F); -111.8 (m, 1F, arom F); -124.6 (br s, 2F, C<sub>6</sub>F<sub>5</sub>); ca. -129 (very br s, 2F, C<sub>6</sub>F<sub>5</sub>); -145.5 (m, 1F, C<sub>6</sub>F<sub>5</sub>); -148.8 (m, 1F, C<sub>6</sub>F<sub>5</sub>); -158.3 (m, 2F, C<sub>6</sub>F<sub>5</sub>); -160.5 (br s, 2F, C<sub>6</sub>F<sub>5</sub>). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C),  $\delta$ : -5.3 (br s). The structure/composition was confirmed by X-ray analysis.

#### Compound 2-v (Table 2)

A mixture of the dichloro-bridged dinuclear bis-cyclometallated Ir complex made with 2-phenylpyridine, prepared as described in Sprouse, S.; King, K. A.; Spellane, P. J.; Watts, R. J., J. Am. Chem. Soc., 1984, 106, 6647-53; Garces, F. O.; King, K. A.; Watts, R. J., Inorg. Chem., 1988, 27, 3464-71 (120 mg), phosphinoalkanol PO-2H from Example 3 (170 mg), DCE (4

mL), and 10% NaOH (1 mL) was vigorously stirred under reflux (N<sub>2</sub>) for 20 min. The reaction mixture was extracted with dichloromethane and the combined organic extracts were filtered through a silica gel column, then evaporated to 1-2 mL and treated with hexanes (8 mL, portionwise). After 4 hours the yellow precipitate was separated and recrystallized from dichloromethane - hexanes, washed with hexanes (3 x 1 mL), and dried under vacuum. Yield: 0.22 g (86%). Anal. Calcd for C<sub>42</sub>H<sub>24</sub>F<sub>18</sub>N<sub>2</sub>IrOP, %: C, 44.3; H, 2.1; N, 2.5. Found, %: C, 43.9; H, 1.6; N, 2.6. <sup>1</sup>H NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 3.1 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = 8.3 Hz, 1H, CH<sub>2</sub>); 3.8 (dd, J<sub>H-H</sub> = 16.2 Hz, J<sub>H-P</sub> = ca. 12.1 Hz, 1H, CH<sub>2</sub>); 6.0 (m, 1H, arom H); 6.7 (m, 1H, arom H); 6.9 (m, 2H, arom H); 7.0 (m, 4H, arom H); 7.2 (m, 2H, arom H); 7.7 (m, 6H, arom H); 7.9 (m, 2H, arom H); 8.1 (m, 2H, arom H); 8.3 (d, 1H, arom H); 8.9 (d, 1H, arom H). <sup>19</sup>F NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: -63.5 (s, 6F, arom CF<sub>3</sub>); -63.8 (s, 6F, arom CF<sub>3</sub>); -75.2 (m, 3F, CF<sub>3</sub>COH); -79.1 (m, 3F, CF<sub>3</sub>COH). <sup>31</sup>P NMR (CD<sub>2</sub>Cl<sub>2</sub>, 20 °C), δ: 14.0 (s).

#### EXAMPLE 8

This example illustrates the formation of an Ir complex of the invention having the Formula I, in a two-step, one-pot method, directly from IrCl<sub>3</sub> (hydrate).

##### 20      Compound 2-f (Table 2)

A mixture of IrCl<sub>3</sub> (hydrate; ca. 54% Ir), arylpyridine 1-ac (12.00 g; 86% purity, contained 14% of 2-chloro-4-methylpyridine starting material), 2-ethoxyethanol (100 mL), and water (20 mL) was stirred under reflux for 2 hours. The solid-free yellow-tan solution was cooled to about 100 °C, treated, at stirring, with a solution of NaOH (3.0 g) in water (20 mL) (the mixture turned dark), and then immediately with phosphinoalkanol PO-1H from Example 2 (6.0 g). The mixture turned yellow and a yellow precipitate formed. Water (100 mL) was added, and the mixture was stirred for 5 min at 110 °C (oil bath). The mixture was allowed to cool to room temperature and then kept at ca. 10 °C overnight. The solid was separated by filtration, washed with water, dried on the filter, and dissolved in ca. 400 mL of warm dichloromethane. The solution was filtered through a silica gel column which was then washed with dichloromethane. The combined organic solutions were reduced in volume to ca. 20-30 mL and treated with hexanes (150 mL). After 2 hours the crystalline pale-yellow precipitate was separated, washed with hexanes (4 x 20 mL), and dried under vacuum. Yield of 2-f: 12.3 g (calculated on Ir). The product was

found to be TLC- and spectroscopically pure ( $^1\text{H}$ ,  $^{19}\text{F}$ , and  $^{31}\text{P}$  NMR; see Example 7).

#### EXAMPLE 9

5 This example illustrates the formation of OLEDs using the iridium complexes of the invention.

Thin film OLED devices including a hole transport layer (HT layer), electroluminescent layer (EL layer) and at least one electron transport layer (ET layer) were fabricated by the thermal evaporation technique. An Edward Auto 306 evaporator with oil diffusion pump was used. The base  
10 vacuum for all of the thin film deposition was in the range of  $10^{-6}$  torr. The deposition chamber was capable of depositing five different films without the need to break up the vacuum.

An indium tin oxide (ITO) coated glass substrate was used, having an ITO layer of about 1000-2000 Å. The substrate was first patterned by  
15 etching away the unwanted ITO area with 1N HCl solution, to form a first electrode pattern. Polyimide tape was used as the mask. The patterned ITO substrates were then cleaned ultrasonically in aqueous detergent solution. The substrates were then rinsed with distilled water, followed by isopropanol, and then degreased in toluene vapor for ~3 hours.

20 The cleaned, patterned ITO substrate was then loaded into the vacuum chamber and the chamber was pumped down to  $10^{-6}$  torr. The substrate was then further cleaned using an oxygen plasma for about 5-10 minutes. After cleaning, multiple layers of thin films were then deposited sequentially onto the substrate by thermal evaporation. Finally,  
25 patterned metal electrodes of Al were deposited through a mask. The thickness of the film was measured during deposition using a quartz crystal monitor (Sycon STC-200). All film thickness reported in the Examples are nominal, calculated assuming the density of the material deposited to be one. The completed OLED device was then taken out of  
30 the vacuum chamber and characterized immediately without encapsulation.

A summary of the device layers and thicknesses is given in Table 5. In all cases the anode was ITO as discussed above, and the cathode was Al having a thickness in the range of 700-760 Å.

35

TABLE 5			
MPMP = bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)-methane DPA = 4,7-diphenyl-1,10-phenanthroline			
Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
9-1	MPMP (538)	Compound 2-a (404)	DPA (408)
9-2	MPMP (511)	Compound 2-a (411)	DPA (410)
9-3	MPMP (575)	Compound 2-c (412)	DPA (402)
9-4	MPMP (511)	Compound 2-d (411)	DPA (411)
9-5	MPMP (535)	Compound 2-e (423)	DPA (412)
9-6	MPMP (526)	Compound 2-f (436)	DPA (404)
9-7	MPMP (505)	Compound 2-g (433)	DPA (408)
9-8	MPMP (544)	Compound 2-h (424)	DPA (412)
9-9	MPMP (548)	Compound 2-i (438)	DPA (725)
9-10	MPMP (510)	Compound 2-k (404)	DPA (414)
9-11	MPMP (504)	Compound 2-o (422)	DPA (387)
9-12	MPMP (512)	Compound 2-p (408)	DPA (402)
9-13	MPMP (546)	Compound 2-q (428)	DPA (411)
9-14	MPMP (516)	Compound 2-r (462)	DPA (408)
9-15	MPMP (508)	Compound 2-s (461)	DPA (412)



TABLE 5			
MPMP = bis[4-(N,N-diethylamino)-2-methylphenyl](4-methylphenyl)-methane DPA = 4,7-diphenyl-1,10-phenanthroline			
Sample	HT layer (Thickness, Å)	EL layer (Thickness, Å)	ET layer (Thickness, Å)
9-16	MPMP (514)	Compound 2-v (406)	DPA (407)

The OLED samples were characterized by measuring their (1) current-voltage (I-V) curves, (2) electroluminescence radiance versus voltage, and (3) electroluminescence spectra versus voltage. The apparatus used, 200, is shown in Figure 7. The I-V curves of an OLED sample, 220, were measured with a Keithley Source-Measurement Unit Model 237, 280. The electroluminescence radiance (in the unit of  $\text{Cd/m}^2$ ) vs. voltage was measured with a Minolta LS-110 luminescence meter, 210, while the voltage was scanned using the Keithley SMU. The electroluminescence spectrum was obtained by collecting light using a pair of lenses, 230, through an electronic shutter, 240, dispersed through a spectrograph, 250, and then measured with a diode array detector, 260. All three measurements were performed at the same time and controlled by a computer, 270. The efficiency of the device at certain voltage is determined by dividing the electroluminescence radiance of the LED by the current density needed to run the device. The unit is in  $\text{Cd/A}$ . The results are given in Table 6 below:

TABLE 6			
Electroluminescent Properties of Iridium Compounds			
Sample	Peak Radiance, $\text{Cd/m}^2$	Peak efficiency, $\text{Cd/A}$	Approximate Peak Wavelengths, nm
9-1	450 at 23 V	4.5	460 and 500
9-2	15 at 20 V	0.6	460 and 490
9-3	450 at 20 V	2.8	465 and 495

<b>TABLE 6</b> <b>Electroluminescent Properties of Iridium Compounds</b>			
Sample	Peak Radiance, Cd/m <sup>2</sup>	Peak efficiency, Cd/A	Approximate Peak Wavelengths, nm
9-4	35 at 20 V	0.4	460 and 480
9-5	900 at 22 V	5.0	470 and 510
9-6	450 at 21 V	12.0	470 and 505
9-7	25 at 23 V	1.0	470 and 500
9-8	400 at 22 V	5.5	470 and 500
9-9	190 at 22 V	1.2	465 and 495
9-10	880 at 22 V	6.0	463 and 490
9-11	700 at 21 V	4.0	480 and 510
9-12	120 at 20 V	0.8	478 and 505
9-13	1500 at 22 V	12.0	470 and 500
9-14	250 at 25 V	1.8	468 and 497
9-15	2400 at 22 V	17.0	500
9-16	250 at 22 V	1.5	483 and 506

CLAIMS

What is claimed is:

1. An organic electronic device comprising an active layer, wherein  
 5 at least 20% by weight of the active layer comprises at least one  
 compound having Formula I below:



where

- 10  $\text{L}^a$  and  $\text{L}^b$  are alike or different and each of  $\text{L}^a$  and  $\text{L}^b$  has  
 Formula II, shown in Figure 1, wherein:

$\text{R}^1$  through  $\text{R}^8$  are independently selected from  
 hydrogen, deuterium, alkyl, alkoxy, halogen, nitro,  
 cyano, fluoro,  $\text{C}_n(\text{H}+\text{F})_{2n+1}$ ,  $\text{OC}_n(\text{H}+\text{F})_{2n+1}$ , and  
 15  $\text{OCF}_2\text{X}$ , where  $n$  is an integer from 1 through 12,  
 and  $\text{X}$  is H, Cl, or Br, and

$\text{A}$  is C or N, provided that when  $\text{A}$  is N, there is no  $\text{R}^1$ ;  
 and

$\text{L}'$  is a bidentate phosphino alkoxide ligand having Formula III,  
 shown in Figure 2, wherein:

20  $\text{R}^9$  can be the same or different at each occurrence and  
 is selected from  $\text{C}_m(\text{H}+\text{F})_{2n+1}$ ,  $\text{C}_6(\text{H}+\text{F})_p\text{Y}_{5-p}$ ,

$\text{R}^{10}$  can be the same or different at each occurrence  
 and is selected from H, F, and  $\text{C}_n(\text{H}+\text{F})_{2n+1}$ ;

25  $\text{Y}$  is  $\text{C}_m(\text{H}+\text{F})_{2m+1}$ ;

$n$  is an integer from 1 through 12;

$m$  is 2 or 3;

$p$  is 0 or an integer from 1 through 5.

- 30 2. The device of Claim 1 wherein  $\text{R}^9$  is selected from  $\text{C}_6\text{F}_5$  and  
 $\text{C}_6\text{H}_p\text{Y}_{5-p}$ , where  $\text{Y}$  is  $\text{CF}_3$  and  $p$  is 3 or 4.

3. The device of Claim 1 wherein at least one of  $\text{R}^{10}$  is  $\text{CF}_3$  and  $m$   
 is 2.

- 35 4. The device of Claim 1 wherein the phosphino alkoxide ligand is  
 selected from 1-diphenylphosphino-2-propoxide; 1,1-bis(trifluoromethyl)-2-  
 (diphenylphosphino)-ethoxide; 1,1-bis(trifluoromethyl)-2-(bis(3'5'-  
 ditrifluoromethylphenyl)phosphino)ethoxide; 1,1-bis(trifluoromethyl)-2-

(bis(4'-trifluoromethylphenyl)phosphino)ethoxide; and 1,1-bis(trifluoromethyl)-2-(bis(pentafluorophenyl)phosphino)ethoxide.

5           5. The organic electronic device of Claim 1, wherein the compound is selected from compounds 2-a through 2-v, as shown in Table 2.

6. A compound selected from compounds 2-a through 2-v, as shown in Table 2.

10           7. A process of preparing a phosphino alkanol comprising the step of combining a dried bromohydrin with n-butyl lithium, wherein the molar ratio of n-butyl lithium to bromohydrin is about 2.

15           8. The process of Claim 7 wherein the epoxide is 1,1-bis(trifluoromethyl)ethylene oxide.

9. The process of Claim 7 wherein the chlorophosphine is chlorodiphenylphosphine.

20           10. A process for preparing a phosphinoalkanol comprising:  
(1) combining an epoxide with aqueous HBr, to form a bromohydrin;  
(2) isolating the bromohydrin from step (1) and removing water;  
(3) combining the dried bromohydrin from step (2) with n-butyl  
lithium, wherein the molar ratio of n-butyl lithium to bromohydrin  
25           is about 2;  
(4) adding a chlorophosphine to the product of step (3); and  
(5) adding acid to the product of step (4).

30           11. A phosphinoalkanol compound prepared by a process comprising the step of combining a dried bromohydrin with n-butyl lithium, wherein the molar ratio of n-butyl lithium to the bromohydrin is about 2.

35           12. A phosphinoalkanol compound prepared by a process comprising:  
(1) combining an epoxide with aqueous HBr, to form a bromohydrin;  
(2) isolating the bromohydrin from step (1) and removing water;

- (3) combining the dried bromohydrin from step (2) with n-butyl lithium, wherein the molar ratio of n-butyl lithium to bromohydrin is about 2;
- (4) adding a chlorophosphine to the product of step (3); and
- 5 (5) adding acid to the product of step (4).

13. The phosphinoalkanol compound of Claim 13 having Formula III-H, shown in Figure 2, wherein:

- 10  $R^9$  can be the same or different at each occurrence and is selected from  $C_m(H+F)_{2n+1}$ ,  $C_6(H+F)_pY_{5-p}$ ,  $R^{10}$  can be the same or different at each occurrence and is selected from H, F, and  $C_n(H+F)_{2n+1}$ ;
- $Y$  is  $C_m(H+F)_{2m+1}$ ;
- $n$  is an integer from 1 through 12;
- 15  $m$  is 2 or 3;
- $p$  is 0 or an integer from 1 through 5.

14. The phosphinoalkanol compound of Claim 11 wherein said compound is selected from 1-diphenylphosphino-2-propanol; 1,1-bis(trifluoromethyl)-2-(diphenylphosphino)-ethanol; 1,1-bis(trifluoromethyl)-2-(bis(3'5'-ditrifluoromethylphenyl)phosphino)ethanol; 1,1-bis(trifluoromethyl)-2-(bis(4'-trifluoromethylphenyl)phosphino)ethanol; and 1,1-bis(trifluoromethyl)-2-(bis(pentafluorophenyl)phosphino)ethanol.

25

1/3

FIG. 1A




FIG. 1B




FIG. 2A





FIG. 2B



2/3




FIG. 3






FIG. 4

FIG. 5A



(IV)

FIG. 5B



(V)

3/3




FIG. 6




FIG. 7



## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 03/04149

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H05B33/14 C09K11/06 H01L51/20 C07F15/00 C07F9/50  
H01L51/30

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H05B C09K H01L C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

CHEM ABS Data, WPI Data, EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02 02714 A (PETROV VIACHESLAV A ;DU PONT (US); WANG YING (US); GRUSHIN VLADIMI) 10 January 2002 (2002-01-10) * page 2, First Formula, page 4, Second Formula, page 6-8, Table 1, compounds IV, V, VI, IX, X *	1-6
A	WO 01 41512 A (UNIV PRINCETON ;UNIV SOUTHERN CALIFORNIA (US)) 7 June 2001 (2001-06-07) cited in the application * the entire document *	1-6
A	US 2001/019782 A1 (KIMURA KEIZO ET AL) 6 September 2001 (2001-09-06) * the entire document *	1-6
	--- -/-- ---	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the International filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&\* document member of the same patent family

Date of the actual completion of the international search

4 June 2003

Date of mailing of the international search report

24/06/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Nemes, C

## INTERNATIONAL SEARCH REPORT

Internationals Application No

PCT/US 03/04149

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GRUSHIN V V ET AL: "New, efficient electroluminescent materials based on organometallic Ir complexes" CHEMICAL COMMUNICATIONS, ROYAL SOCIETY OF CHEMISTRY, GB, 2001, pages 1494-1495, XP002196401 ISSN: 1359-7345 * the entire document *	1-6
X	MARSI, K.L.; CO-SARNO, M.E.: "Synthesis, Structure Analysis, and Stereochemistry of Some Reactions of cis- and trans-2,2,5-Trimethyl-3-phenyl-1,3-oxaphospholane" JOURNAL OF ORGANIC CHEMISTRY, vol. 42, no. 5, 1977, pages 778-781, XP002243253 * page 779, compound 11 *	13,14
X	BOERÉ, R.T. ET AL.: "Complexes of Hybrid Ligands. Synthesis of Fluoro-Alcohol Diarylphosphino Ligand and Its Complexes with Pt <sup>2+</sup> , Pd <sup>2+</sup> , Ni <sup>2+</sup> , Co <sup>2+</sup> , Cu <sup>+</sup> , and Rh <sup>3+</sup> : Crystal and Molecular Structure of a Trans Square-Planar Ni <sup>2+</sup> Complex with Two Bidentate Ligands Showing Cis-Trans Isomerism in Solution" INORGANIC CHEMISTRY, vol. 24, no. 22, 1985, pages 3680-3687, XP002243254 cited in the application * page 3684, reaction scheme *	13,14
P,X	GRUSHIN V V ET AL: "Facile preparation and synthetic applications of LiCH <sub>2</sub> C(CF <sub>3</sub> ) <sub>2</sub> OLi" JOURNAL OF FLUORINE CHEMISTRY, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 117, no. 2, 28 October 2002 (2002-10-28), pages 121-129, XP004389686 ISSN: 0022-1139 * page 122. Scheme 1 *	13,14

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US 03/04149

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 7-12  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:  
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

### Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

Continuation of Box I.2

Claims Nos.: 7-12

Present claims 7-12 lack clarity within the meaning of Article 6 PCT to such an extent as to render a meaningful search of the claims impossible. The claims are unclear concerning the dependencies: claims 8 and 9 have no antecedent basis in claim 7. It could be that claim 10 should be the first independent process claim with dependent claims 7, 8, 9. Claim 11 is an independent product claim on the basis of claim 7. Concerning the above said, in consequence, the status of dependency of claim 11 is also not clear. Claim 12 is an independent product claim on the basis of claim 10. The status of dependency is here again not clear.

Consequently, the search has been carried out for those parts of the application which do appear to be clear, namely claims 1-6 and 13-14.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

**INTERNATIONAL SEARCH REPORT**  
 information on patent family members

International Application No

PCT/US 03/04149

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0202714	A	10-01-2002	AU 7155001 A	14-01-2002
			EP 1295514 A2	26-03-2003
			WO 0202714 A2	10-01-2002
			US 2002190250 A1	19-12-2002
			US 2002121638 A1	05-09-2002
<hr/>				
WO 0141512	A	07-06-2001	AU 1807201 A	12-06-2001
			CN 1413426 T	23-04-2003
			EP 1252803 A1	30-10-2002
			WO 0141512 A1	07-06-2001
			US 2003017361 A1	23-01-2003
			US 2002034656 A1	21-03-2002
<hr/>				
US 2001019782	A1	06-09-2001	JP 2001345183 A	14-12-2001
			JP 2001247859 A	14-09-2001
<hr/>				